

RG 104, Sequence 27

8NN-104-86-027, Register of All Gold &
Silver Assays, 1905 - 1971.

Assayer's Register of Mint Finegold; 1923-1952

Form No. 764

ASSAYER'S REGISTER

of

MINT FINE GOLD

U. S. MINT, DENVER





ASSAYER'S REPORT


FOR MOR-C-17-Sub. Com.


Material Certificate Bars F.Y. 1966

Date June 2 1966

No.	Fineness		No.	Fineness	
	Gold	Silver		Gold	Silver
1	9971		19	9973	
2	9972		20	9973	
3	9965		21	9970	
4	9978		22	9976	
5	9978		23	9973	
6	9977		24	9974	
7	9975		25	9975	
8	9974		26	9973	
9	9977		27	9974	
10	9975		28	9975	
11	9976		29	9973	
12	9974		30	9975	
13	9972		31	9975	
14	9975		32	9974	
15	9974		33	9973	
16	9970		34	9978	
17	9971		35	9973	
18	9970		36	9975	

E.A.
Assayer





ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE	No. OF MELT.	FINESS.	DATE	No. OF MELT.	FINESS.
1923					
Oct 5	1	999 80	12/5/23	33	999 9
	2	999 75	"	34	999 9
10/12/23	3	999 9	"	35	999 9
"	4	999 9	12/7/23	36	999 9
"	5	999 9	"	37	999 9
10/17/23	6	999 7	"	38	999 9
"	7	999 9	1/11/24	39	999 9
"	8	999 8	"	40	999 9
10/24/23	9	999 9	"	41	999 9
"	10	999 9	"	42	999 9
"	11	999 9	1/16/24	43	999 9
"	12	999 9	"	44	999 9
11/1/23	13	999 8	"	45	999 9
"	14	999 9	"	46	999 9
"	15	999 9	1/23/24	47	999 9
"	16	999 9	"	48	999 9
11/6/23	17	999 9	"	49	999 9
"	18	999 8	"	50	999 9
"	19	999 8	1/29/24	51	999 8
"	20	999 8	"	52	999 8
11/13/23	21	999 8	"	53	999 8
"	22	999 9	"	54	999 9
"	23	999 9	2/5/24	55	999 8
"	24	999 9	"	56	999 8
11/20/23	25	999 9	"	57	999 9
"	26	999 9	"	58	999 9
"	27	999 9	2/9/24	59	999 9
"	28	999 9	"	60	999 8
11/27/23	29	999 9	"	61	999 8
"	30	999 9	"	62	999 8
"	31	999 9	2/10/24	63	999 9
"	32	999 9	"	64	999 9

Three receipts with each melt

Three receipts with each melt

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	NO. OF MELT.		FINESS.	DATE.	NO. OF MELT.		FINESS.
2/15/24	65		999 8	4/23/24	97		999 9
"	66		999 8	"	98		999 9
2/21/24	67		999 9	4/20/24	99		999 9
"	68		999 9	"	100		999 9
"	69		999 9	"	1		999 9
"	70		999 9	"	2		999 9
3/1/24	71		999 9	5/17/24	3		999 8
"	72		999 9	"	4		999 9
"	73		999 9	"	5		999 9
"	74		999 9	"	6		999 9
3/12/24	75		999 8	5/13/24	7		999 8
"	76		999 8	"	8		999 9
"	77		999 8	"	9		999 8
"	78		999 8	"	110		999 9
3/19/24	79		999 9	5/20/24	1		999 8
"	80		999 9	"	2		999 8
"	81		999 9	"	3		999 8
"	82		999 9	"	4		999 9
4/1/24	83		999 9	5/22/24	5		999 8
"	84		999 9	"	6		999 8
"	85		999 9				
"	86		999 9				
4/8/24	87		999 9				
"	88		999 9				
"	89		999 9				
"	90		999 9				
4/16/24	91		999 9				
"	92		999 9				
"	93		999 9				
"	94		999 9				
4/23/24	95		999 9				
"	96		999 9				

Three samples with each melt

Three samples to the melt

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	NO. OF MELT.	FINESS.	DATE.	NO. OF MELT.	FINESS.
<i>Three samples with each melt</i>					
1924					
8/26/24	1	999 9	11/17/24	33	999 8
"	2	999 9		34	999 9
"	3	999 9		35	999 9
"	4	999 9		36	999 9
9/6/24	5	999 9	11/25/24	37	999 9
"	6	999 9	"	38	999 8
"	7	999 9	"	39	999 9
"	8	999 9	"	40	999 9
9/17/24	9	999 9	12/8/24	1	999 9
"	10	999 9	"	2	999 8
"	11	999 9	"	3	999 9
"	12	999 9	"	4	999 9
9/26/24	13	999 9	12/7/24	5	999 9
"	14	999 9	"	6	999 9
"	15	999 9	"	7	999 9
"	16	999 9	"	8	999 9
10/8/24	17	999 9	12/24/24	9	999 9
"	18	999 9	"	50	999 9
"	19	999 9	"	1	999 9
"	20	999 9	1/9/25	2	999 9
10/16/24	21	999 9	1/7/25	3	999 9
"	22	999 9	"	4	999 9
"	23	999 9	"	5	999 9
"	24	999 9	"	6	999 9
10/27/24	25	999 9	1/17/25	7	999 9
"	26	999 9	"	8	999 9
"	27	999 9	"	9	999 9
"	28	999 9	"	60	999 9
11/6/24	29	999 8	1/24/25	1	999 9
"	30	999 9	"	2	999 9
"	31	999 9	"	3	999 9
"	32	999 9	"	4	999 9

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	No. OF MELT.	FINENESS.	DATE.	No. OF MELT.	FINENESS.
<i>Three samples with each melt</i>					
2/10/25	65	999 9	5/1/25	97	999 9
"	6	999 9	"	8	999 9
"	7	999 9	"	9	999 9
"	8	999 9	"	100	999 9
2/18/25	9	999 9	5/6/25	1	999 9
"	90	999 9	"	2	999 9
"	1	999 9	"	3	999 9
"	2	999 9	"	4	999 9
2/28/25	3	999 9	5/14/25	5	999 9
"	4	999 9	"	6	999 9
"	5	999 9	"	7	999 9
"	6	999 9	"	8	999 9
3/12/25	7	999 9			
"	8	999 9			
"	9	999 9			
"	80	999 9			
3/19/25	1	999 9			
"	2	999 9			
"	3	999 9			
"	4	999 9			
3/31/25	5	999 9			
"	6	999 9			
"	7	999 9			
"	8	999 9			
4/19/25	9	999 9			
"	90	999 9			
"	1	999 9			
"	2	999 9			
4/23/25	3	999 9			
"	4	999 8			
"	5	999 9			
"	6	999 9			

ASSAYER'S REGISTER OF MINT FINE GOLD.

9-2231

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1926			1928		
3/24	64	999 9	5/15	29	999 9
	5	999 9		30	999 9
	6	999 9	5/22	1	999 9
1928				2	999 9
1/27	1	999 9		3	999 9
	2	999 9	5/24	4	999 9
	3	999 9			
	4	999 9	1929		
2/21	5	999 9		1	999 7
	6	999 9		2	999 9
	7	999 9		3	999 9
	8	999 9		4	999 9
2/28	9	999 9	2/11	5	999 9
	10	999 9		6	999 9
	1	999 9	2/28	7	999 9
3/20	2	999 9		8	999 9
	3	999 9		9	999 9
	4	999 9		10	999 9
	5	999 9	3/13	1	999 9
3/31	6	999 9		2	999 9
	7	999 9		3	999 9
	8	999 9		4	999 9
	9	999 9	3/27	5	999 9
4/20	20	999 9		6	999 9
	1	999 9		7	999 9
	2	999 9		8	999 9
	3	999 9	4/19	9	999 9
4/30	4	999 9		20	999 9
	5	999 9		1	999 9
	6	999 9		2	999 9
5/15	7	999 9	4/23	3	999 9
	8	999 9		4	999 9

ASSAYER'S REGISTER OF MINT FINE GOLD.

9-2231

DATE.	NO. OF MELT.	FINESS.	DATE.	NO. OF MELT.	FINESS.
1929			1930		
4/23	25	999 9	1/29	1	999 9
	6	999 9		2	999 9
5/8	7	999 9		3	999 9
	8	999 9		4	999 9
	9	999 9	1/31	5	999 9
	30	999 9	2/12	6	999 9
5/20	1	999 9		7	999 9
	2	999 9		8	999 9
	3	999 9		9	999 9
	4	999 9	2/28	10	999 9
5/24	5	999 9		1	999 9
	6	999 9		2	999 9
	7	999 9		3	999 9
	8	999 9		4	999 9
6/7	9	✓ 999 9	3/18	5	999 9
				6	999 9
				7	999 9
				8	999 9
			3/28	9	999 9
				20	999 9
1930				1	999 9
5/13	33	999 9		2	999 9
	4	999 9		3	999 9
	5	999 9		4	999 9
	6	999 9	4/15	5	999 9
5/27	7	999 9		6	999 9
	8	999 9		7	999 9
	9	999 9		8	999 9
	40	999 9	4/30	9	999 9
	1	999 9		30	999 9
5/29	2	✓ 999 9		1	999 9
	3	✓ 999 9		2	999 9

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2231

DATE.	NO. OF MELT.	Sent to Bureau.	FINESS.	DATE.	NO. OF MELT.	FINESS.
1930				1930		
8/29	1		999 9	12/31	33	999 9
	2		999 9		34	999 9
	3		999 9	1931		
	4		999 9	1/15	35	999 9
	5		999 9		6	999 9
9/19	6		999 9		7	999 9
	7		999 9	1/31	8	999 9
	8		999 9		9	999 9
	9		999 9		40	430-35 ✓ 40-1820
9/30	10	.40 ✓	999 9		1	999 9
	1		999 9	2/16	2	999 9
	2		999 9		3	999 9
	3		999 9		4	999 9
10/17	4		999 9	3/1	5	.44 ✓ 999 9
	5	.60 ✓	999 9		6	999 9
	6		999 9		7	999 9
10/28	7		999 9		8	999 9
	8		999 9	3/18	9	999 9
	9		999 9		50	.33 ✓ 999 9
	20	.54 ✓	999 9		1	999 9
11/14	1		999 9	3/31	2	999 9
	2		999 9		3	999 9
	3		999 9		4	999 9
12/1	4		999 9		5	.39 ✓ 999 9
	5	.87 ✓	999 9	4/18	6	999 9
	6		999 9		7	999 9
	7		999 9		8	999 9
12/16	8		999 9	4/29	9	999 9
	9		999 9		60	.53 ✓ 999 9
	30		999 9		1	999 9
12/31	1		999 9	5/8	2	999 9
	2		999 9		3	999 9

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2231

DATE.	No. OF MELT.		FINESS.	DATE.	No. OF MELT.	FINESS.
1931				1931		
5/7	64		999 9	12/30	27	999 9
5/15	5	48	999 9	1932 1/20	8	999 9
	6		999 9		9	999 9
	7		999 9		30	59 999 9
	8		999 9	1/29	1	999 9
1931					2	999 9
Sept 22	1		999 9		3	999 9
	2		999 9		4	999 9
	3		999 9	2/17	5	57 999 9
9/30	4		999 9		6	999 9
	5	52	999 9		7	999 9
	6		999 9	2/26	8	999 9
10/15	7		999 9		9	999 9
	8		999 9		40	66 999 9
	9		999 9		1	999 9
10/30	10	74	999 9	3/16	2	999 9
	1		999 9		3	999 9
	2		999 9		4	999 9
	3		999 9	3/30	5	999 9
11/17	4		999 9		6	999 9
	5	67	999 9		7	999 9
	6		999 9		8	999 9
12/1	7		999 9	4/15	9	999 9
	8		999 9		50	999 9
	9		999 9		1	999 9
	20	58	999 9	4/28	2	999 9
12/16	1		999 9		3	999 9
	2		999 9		4	999 9
	3		999 9		5	999 9
12/30	4		999 9	5/12	6	999 9
	5	59	999 9		7	999 9
	6		999 9		8	999 9

2.69.00.
45.00.00-60. Returned.

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2291

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1932			1932		
5/18	59	999 9	12/14	27	999 9
	60	999 9		8	999 9
	1	999 9		9	999 9
	2	999 9		30	999 9
1932			12/21	1	999 9
9/2	1	999 9		2	999 9
9/15	2	999 9		3	999 9
	3	999 9		4	999 9
	4	999 9	12/29	5	999 9
9/24	5	999 9		6	999 9
	6	999 9		7	999 9
9/27	7	999 9	1933	8	999 9
	8	999 9	1/17	9	999 9
	9	999 9	1/20	40	999 9
10/13	10	999 9		1	999 9
	1	999 9	1/23	2	999 9
10/26	2	999 9		3	999 9
	3	999 9	1/30	4	999 9
	4	999 9		5	999 9
	5	999 9		6	999 9
10/29	6	999 9	2/11	7	999 9
	7	999 9		8	999 9
11/10	8	999 9	3/8	9	999 9
	9	999 9		50	999 9
	20	999 9	2/28	1	999 9
11/15	1	999 9		2	999 9
	2	999 9		3	999 9
11/30	3	999 9		4	999 9
	4	999 9		5	999 9
	5	999 9	3/8	6	999 9
	6	999 9		7	999 9

Blanca
291 opp
Returned
2/17/23

Balance
299.00
Returned
5/12/23.

ASSAYER'S REGISTER OF MINT FINE GOLD.

9-2231

DATE	No. OF MELT.	FINESS.	DATE	No. OF MELT.	FINESS.
1933			1933		
3/14	58	999 9	9/30	11	999 9
	9	999 9		12	999 9
3/21	60	999 9	10/0	13	999 9
	1	999 9		14	999 9
3/28	2	999 9	10/24	15	999 9
	3	999 9		16	999 9
	4	999 9	10/26	17	999 9
4/7	5	999 9		18	999 9
	6	999 9	10/31	19	999 9
4/18	7	999 9		20	999 9
	8	999 9	11/7	1	999 9
	9	999 9		2	999 9
	70	999 9	11/20	3	999 9
4/28	1	999 9		4	999 9
	2	999 9	11/28	5	999 9
	3	999 9		6	999 9
	4	999 9		7	999 9
	5	999 9		8	999 9
		✓ 999 9	12/12	9	999 9
				30	999 9
			12/29	1	999 9
				2	999 9
1933				3	999 9
8/14	1	999 9	12/29	4	999 9
	2	999 9		5	999 9
8/29	3	999 9		6	999 9
	4	999 9	1/6/34	7	999 9
8/31	5	999 9		8	999 9
	6	999 9		9	999 9
9/16	7	999 9	1/8	40	999 9
	8	999 9	1/18	1	999 9
9/23	9	999 9		2	999 9
	10	999 9			

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2231

DATE	No. OF MELT.	FINESS.	DATE	No. OF MELT.	FINESS.
1934			1938		
1/26	43	999 9	2/2	1	999 8
"	44	999 9		2	999 7
2/2	45	999 9		3	999 7
	46	999 9		4	999 7
2/9	7	999 9	2/4	5	999 8
	8	999 9		6	999 8
	9	999 9		7	999 8
2/15	50	999 9	2/10	8	999 8
	1	999 9		9	999 9
2/27	2	999 9		10	999 9
	3	999 9	2/14	1	999 8
3/30	4	999 9		2	999 8
	5	999 9		3	999 8
	6	999 9	2/17	4	999 8
	7	999 9		5	999 9
	8	999 9		6	999 8
	9	999 9	2/24	7	999 8
	60	999 9		8	999 8
	1	999 9		9	999 8
	2	999 9	2/28	20	999 8
4/23	3	999 9	3/5	1	999 8
	4	999 9		2	999 8
	5	999 9		3	999 8
	6	999 9	3/11	4	999 8
	7	999 9		5	999 8
	8	999 9		6	999 9
	9	999 9	3/17	7	999 8
	70	999 9		8	999 8
	1	999 9		9	999 9
	2	999 9	3/24	30	999 9
				1	999 9
				2	999 9

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-251

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1938			1938		
	33	999 9	8/2	1	999 3
	4	999 8		2	999 2
	5	999 8		3	999 1
3/31	6	999 8		4	999 5
4/7	7	999 7		5	999 7
	8	999 7		6	999 7
	9	999 8	8/11	7	999 7
4/12	40	999 8		8	999 7
	1	999 7		9	999 8
	2	999 8		10	999 8
4/16	3	999 7	8/18	1	999 5
	4	999 8		2	999 5
	5	999 8		3	999 7
4/20	6	999 8		4	999 8
	7	999 8		5	999 8
	8	999 8		6	999 7
4/28	9	999 8	8/22	7	999 9
	50	999 8		8	999 8
	1	999 7		9	999 8
5/7	2	999 8	8/25	20	999 8
	3	999 8		1	999 8
	4	999 8		2	999 8
5/1	5	999 8	8/30	3	999 8
	6	999 8		4	999 8
	7	999 8		5	999 9
5/19	8	999 7	9/2	6	999 8
	9	999 7		7	999 8
	60	999 7	9/6	8	999 8
5/21	1	899 8	9/8	9	999 9
*	2	899 8		30	999 8
*			9/13	1	999 8
				2	999 9

* 61-62
called certificate
Bar Corn

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1938			1938		
9/9	33	9998 ✓		65	9999 ✓
	34	9999 ✓		6	9999 ✓
9/19	35	9999 ✓ "11		7	9999 ✓
	36	9999 ✓		8	9999 ✓
	37	9999 ✓		9	9999 ✓
9/22	38	9998 ✓ "17		70	9999 ✓
	39	9998 ✓		1	9999 ✓
	40	9998 ✓		2	9999 ✓
9/26	1	9999 ✓ "14		3	9999 ✓
	2	9999 ✓		4	9999 ✓
	3	9999 ✓		5	9999 ✓
9/27	4	9998 ✓		6	9999 ✓
	5	9998 ✓		7	9998 ✓
	6	9998 ✓		8	9998 ✓
9/30	7	9999 ✓ "121		9	9998 ✓
10/4	8	9998 ✓		80	9998 ✓
10/6	9	9999 ✓		1	9998 ✓
	50	9999 ✓ "125		2	9999 ✓
	1	9999 ✓		3	9999 ✓
10/12	2	9999 ✓		4	9999 ✓
	3	9999 ✓ "129		5	9999 ✓
	4	9998 ✓		6	9999 ✓
	5	9999 ✓		7	9999 ✓
	6	9999 ✓ "12		8	9999 ✓
	7	9999 ✓		9	9998 ✓
10/19	8	9999 ✓		90	9999 ✓
	9	9999 ✓		1	9998 ✓
	60	9999 ✓ "126		2	9998 ✓
10/25	1	9999 ✓		3	9999 ✓
	2	9998 ✓ "1212		4	9998 ✓
	3	9999 ✓		5	9998 ✓
10/26	4	9999 ✓		6	9998 ✓

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2291

DATE 1938	No. OF MELT.	FINESS.	DATE 1939	No. OF MELT.	FINESS.	
12/16	97	999 9	129	999 9		
	8	999 8	130	999 9		
	9	999 8	1	999 8		
	100	999 8	2	999 9		
	1	999 8	2/3	3	999 8	
	2	999 8	4	999 8		
12/22	3	999 8	5	999 8		
	4	999 9	12/8	6	999 8	
	5	999 8	7	999 9		
12/29	6	999 9	12/9	8	999 8	
	7	999 8	9	999 8		
	8	999 8	140	999 8		
	9	999 8	1	999 8		
	110	999 8	12/15	2	999 8	
	1	999 8	3	999 8		
1/6/39	2	999 9	4	999 8		
	3	999 9	12/17	5	999 9	
	4	999 8	6	999 8		
1/11	5	999 9	7	999 8		
	6	999 9	12/23	8	999 8	
	7	999 9	9	999 9		
1/12	8	999 9	150	999 8		
	9	999 9	12/27	1	999 8	
	120	999 8	2	999 8		
1/19	1	999 9	3	999 8		
	2	999 9	3/6	4	999 8	
	3	999 8	5	999 8		
1/25	4	999 9	6	999 9		
	5	999 9	7	999 8		
1/26	6	999 8	8	999 8		
	7	999 7	9	999 8		
	8	999 9	13/1	160	999 9	

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2231

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1939					
	161	999 8	9/8	16	999 9 ✓
	2	999 9		7	999 8 ✓
3/15	3	999 8		8	999 8 ✓
	4	999 8	9/11	9	999 9 ✓
	5	999 8		20	999 9 ✓
3/16	6	999 9		1	999 8 ✓
	7	999 8	9/14	2	999 8 ✓
	8	999 8		3	999 8 ✓
3/27	9	999 8		4	999 9 ✓
	170	999 8	9/20	5	999 9 ✓
	1	999 8		6	999 9 ✓
	2	999 8		7	999 9 ✓
	3	999 8	9/22	8	999 9 ✓
3/28	4	999 8		9	999 9 ✓
	5	999 8		30	999 9 ✓
Aug.	1	999 9	9/27	1	999 8 ✓
	2	999 9		2	999 9 ✓
	3	999 9		3	999 9 ✓
	4	999 9	10/2	4	999 9 ✓
	5	999 9		5	999 9 ✓
	6	999 9		6	999 8 ✓
8/24	7	999 9	10/4	7	999 9 ✓
	8	999 9		8	999 9 ✓
	9	999 9		9	999 9 ✓
8/30	10	999 8	10/9	40	999 9 ✓
	11	999 9		1	999 9 ✓
	12	999 8		2	999 9 ✓
9/1	13	999 8	10/16	3	999 8 ✓
	14	999 8		4	999 9 ✓
	15	999 8		5	999 9 ✓
			10/18	6	999 9 ✓
				7	999 9 ✓

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1939			1939		
	48	999 9		80	999 9
10/23	9	999 9	12/5	1	999 9
	50	999 9		2	999 9
	1	999 8		3	999 9
10/27	2	999 9	12/8	4	999 9
	3	999 9		5	999 9
	4	999 9		6	999 9
10/30	5	999 9	12/11	7	999 9
	6	999 9		8	999 9
11/1	7	999 9		9	999 9
	8	999 9	12/14	90	999 9
	9	999 9		1	999 9
11/6	60	999 9		2	999 9
	1	999 9	12/18	3	999 9
	2	999 9		4	999 9
11/8	3	999 9		5	999 9
	4	999 9	12/21	6	999 9
	5	999 9		7	999 8
11/14	6	999 9		8	999 9
	7	999 9	12/26	9	999 9
11/16	8	999 9		100	999 8
	9	999 9		1	999 9
	70	999 9	12/29	2	999 9
	1	999 9		3	999 9
11/24	2	999 9	1/3/40	4	999 9
	3	999 9		5	999 9
	4	999 9		6	999 9
	5	999 9		7	999 9
	6	999 9	1/12/40	8	999 9
	7	999 8		9	999 9
	8	999 9	1/15	110	999 8
12/1	9	999 9		1	999 8

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	NO. OF MELT.	FINESS.	DATE.	NO. OF MELT.	FINESS.
1940			1940		
	112	999 9		144	999 8
	113	999 8		5	999 9
1/17	4	999 9	2/27	6	999 8
	5	999 9	2/29	7	999 8
	6	999 9		8	999 8
7/19	7	999 9	3/6	9	999 8
	8	999 9		150	999 8
	9	999 8		1	999 9
1/26	120	999 9		2	999 8
	1	999 8	3/11	3	999 9
	2	999 9		4	999 9
	3	999 8		5	999 9
	4	999 9	3/12	6	999 9
	5	999 9		7	999 9
2/2	6	999 9		8	999 9
	7	999 9	3/18	9	999 9
	8	999 9		160	999 9
2/7	9	999 8		1	999 9
	130	999 8	3/21	2	999 9
	1	999 9		3	999 9
	2	999 9		4	999 9
	3	999 9	3/25	5	999 9
	4	999 8		6	999 9
	5	999 9		7	999 9
	6	999 9	3/29	8	999 9
	7	999 9		9	999 9
2/15	8	999 9		170	999 9
	9	999 8	4/10	1	999 8
2/26	140	999 8		2	999 9
	1	999 8		3	999 9
	2	999 8		4	999 9
	3	999 9		5	999 8

ASSAYER'S REGISTER OF MINT FINE GOLD.

0-2031

DATE	No. OF MELT.	FINENESS.	DATE	No. OF MELT.	FINENESS.
1940			1940		
	176	999 9	8/29	1	999 9 ✓
	7	999 9 ✓		2.	999 9 ✓
	8	999 9		3.	999 9 ✓
	9	999 9 ✓		4	999 9 ✓
4/15	180	999 9 ✓		5	999 9 ✓
	1	999 9 ✓		6	999 9 ✓
	2	999 9 ✓		7	999 9 ✓
4/16	3	999 9 ✓		8	999 9 ✓
	4	999 9		9	999 9 ✓
	5	999 9 9/11	10		999 9 ✓
4/18	6	999 9 ✓	1		999 9 ✓
	7	999 8 ✓	2		999 9 ✓
	8	999 9 9/16	3		999 9 ✓
4/24	9	999 9 ✓	4		999 9 ✓
	190	999 9	5		999 9 ✓
4/25	1	999 9 9/20	6		999 9 ✓
	2	999 9	7		999 9 ✓
5/2	3	999 9 (F. 5/2)	8		999 9 ✓
5/3	4	999 9 9/26	9		999 9 ✓
	5	999 9 ✓	20		999 9 ✓
	6	999 9 ✓	1		999 9 ✓
5/8	7	999 9 ✓	2		999 9 ✓
	8	999 9 9/30	3		999 9 ✓
	9	999 9 ✓	4		999 9 ✓
5/9	200	999 9 ✓	5		999 9 ✓
	1	999 9 10/1	6		999 9 ✓
	2	999 9 ✓	7		999 9 ✓
5/10	3	999 9 ✓	8		999 9 ✓
	4	999 9 10/7	9		999 9 ✓
	5	999 9 ✓	30		999 9 ✓
			1		999 9 ✓
			32		999 9 ✓
			10/11		

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	NO. OF MELT.	FINESS.	DATE.	NO. OF MELT.	FINESS.
1940			1940		
10/11	33	9999	11/27	65	9999
	4	9999		6	9999
10/17	5	9999		7	9999
	6	9999		8	9999
	7	9999		9	9999
	8	9999	End Nov.	70	9999
	9	9999	12/2	1	9999
	40	9999		2	9999
10/21	1	9999		3	9999
	2	9999	12/5	4	9999
	3	9999		5	9999
10/24	4	9999		6	9999
	5	9999	12/9	7	9999
End Oct.	6	9999		8	9999
10/29	7	9999		9	9999
	8	9999	12/1	80	9999
11/4	9	9999		1	9999
	50	9999		2	9999
	1	9999	12/16	3	9999
	2	9999		4	9999
11/5	3	9999		5	9999
	4	9999	12/20	6	9999
	5	9999		7	9999
11/12	6	9999	End Oct.	8	9999
	7	9999	12/26	9	9999
	8	9999		90	9999
11/15	9	9999		1	9999
	60	9999	12/27	2	9999
	1	9999		3	9999
11/20	2	9999		4	9999
	3	9999	12/41	5	9999
	4	9999		6	9999

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2231

DATE.	No. OF MELT.	FINENESS.	DATE.	No. OF MELT.	FINENESS.
1941			1941		
	97	999 9		129	999 9
1/3	8	999 9		130	999 9
	9	999 9	2/21	1	999 8
	100	999 9		2	999 9
1/9	1	999 9	End Feb 7	3	999 9
	2	999 9	12/25	4	999 8
	3	999 9		5	999 8
1/13	4	999 9		6	999 8
	5	999 9	2/26	7	999 8
	6	999 9		8	999 9
1/14	7	999 9		9	999 9
	8	999 9	3/4	140	999 8
	9	999 9		1	999 9
1/23	110	999 9		2	999 8
	1	999 9	3/7	3	999 9
	2	999 9		4	999 9
	3	999 9		5	999 8
	4	999 9	3/12	6	999 8
End Jan 7	5	999 9		7	999 9
1/28	6	999 9		8	999 8
	7	999 9	3/14	9	999 9
2/4	8	999 9		150	999 9
	9	999 9		1	999 9
	120	999 9	3/19	2	999 8
	1	999 9		3	999 9
2/10	2	999 9		4	999 9
	3	999 9	3/24	5	999 8
	4	999 9		6	999 9
2/13	5	999 9	End March 27	7	999 9
	6	999 9	3/27	8	999 9
	7	999 9		9	999 9
	8	999 9		160	999 9

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE	NO. OF MELT.	FINESS.	DATE	NO. OF MELT.	FINESS.
1941			1941		
3/31	161	999 9	9/29	1	999 8
	2	999 9		2	999 8
4/3	3	999 9		3	999 8
	4	999 9	10/1	4	999 8
	5	999 9		5	999 8
	6	999 9		6	999 8
4/8	7	999 9		7	999 8
	8	999 9		8	999 8
	9	999 9		9	999 8
4/15	170	999 9	10/3	10	999 9
	1	999 9		1	999 8
	2	999 9	10/6	2	999 8
4/16	3	999 9	10/9	3	999 9
	4	999 9		4	999 8
	5	999 9		5	999 9
4/23	6	999 8		6	999 9
	7	999 8		7	999 8
End Apr	8	999 8		8	999 8
4/30	9	999 9	10/14	9	999 9
	180	999 8		20	999 9
	1	999 9		1	999 9
	2	999 9	10/17	2	999 9
	3	999 8		3	999 9
	4	999 8		4	999 9
5/1	5	999 8	10/21	5	999 9
5/5	6	999 9		6	999 9
	7	999 9		7	999 9
	8	999 8	10/23	8	999 9
End May	9	999 9		9	999 9
				30	999 8
			10/24	1	999 9
				2	999 9

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2241

DATE	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1941			1941		
	33	999 9		65	999 9
	4	999 9		6	999 9
	5	999 9	12/3	7	999 9
End Dec →	6	999 9		8	999 9
11/5	7	999 9		9	999 9
	8	999 9	12/5	70	999 9
	9	999 9	12/7	1	999 9
	40	999 9		2	999 9
	1	999 9		3	999 9
	2	999 8		4	999 9
11/10	3	999 9		5	999 9
	4	999 9	12/11	6	999 9
	5	999 9		7	999 8
11/12	6	999 9		8	999 9
	7	999 8		9	999 9
	8	999 8		80	999 8
	9	999 9		1	999 8
	50	999 9	12/16	2	999 8
	1	999 9		3	999 8
11/17	2	999 9		4	999 8
	3	999 8	12/26	5	999 9
	4	999 9		6	999 9
11/19	5	999 8		7	999 9
	6	999 9		8	999 8
	7	999 9		9	999 9
11/25	8	999 9		90	999 9
	9	999 9		1	999 9
End Nov →	60	999 9		2	999 9
12/2	1	999 9	End Dec	3	999 9
	2	999 9	12/31	4	999 9
	3	999 9		5	999 9
	4	999 9		6	999 9

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2084

DATE.	NO. OF MELT.	FINENESS.	DATE.	NO. OF MELT.	FINENESS.
1942			1942		
1/2	97	999 9	12/3	129	999 8
	98	999 9		130	999 9
	99	999 9		1	999 8
1/5/42	100	999 9		2	999 8
	1	999 8		3	999 8
	2	999 8		4	999 8
1/8	3	999 8	2/6	5	999 8
	4	999 8		6	999 8
	5	999 8		7	999 8
	6	999 9	2/10	8	999 9
	7	999 9		9	999 9
	8	999 8		140	999 9
	9	999 8	2/13	1	999 9
	10	999 8		2	999 9
	1	999 9		3	999 9
	2	999 9	2/17	4	999 8
1/13	3	999 9		5	999 8
1/20	4	999 9		6	999 9
	5	999 8	2/23	7	999 9
	6	999 9		8	999 9
	7	999 9		9	999 9
	8	999 9	2/24	150	999 8
	9	999 8		1	999 9
1/21	120	999 8		2	999 8
	1	999 9		3	999 8
	2	999 8		4	999 8
1/27	3	999 9	Fin. Feb	5	999 9
	4	999 9	3/3	6	999 8
	5	999 9		7	999 9
	6	999 8		8	999 8
	7	999 9		9	999 9
	8	999 8		160	999 8

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2231

DATE.	NO. OF MELT.	FINENESS.	DATE.	NO. OF MELT.	FINENESS.
1942			1942		
	161	999 8	4/7	193	999 9 ✓
3/4	2	999 8		4	999 9 ✓
	3	999 8	4/9	5	999 8 ✓
	4	999 8		6	999 9 ✓
3/10	5	999 8		7	999 9 ✓
	6	999 8		8	999 9 ✓
	7	999 9		9	999 9 ✓
3/11	8	999 8		200	999 9 ✓
	9	999 8	4/15	1	999 8 ✓
	170	999 8		2	999 8 ✓
3/16	1	999 9		3	999 9 ✓
	2	999 9	4/20	4	999 9 ✓
	3	999 8		5	999 9 ✓
3/17	4	999 8		6	999 9 ✓
	5	999 9	4/22	7	999 9 ✓
	6	999 9		8	999 8 ✓
3/20	7	999 8		9	999 9 ✓
	8	999 8	4/28	210	999 9 ✓
	9	999 9		1	999 9 ✓
3/24	180	999 8		2	999 9 ✓
	1	999 9		3	999 8 ✓
	2	999 8		4	999 9 ✓
3/25	3	999 8		5	999 9 ✓
	4	999 9	4/30	6	999 9 ✓
	5	999 9		7	999 9 ✓
	6	999 8		8	999 9 ✓
3/30	7	999 8	5/5	9	999 9 ✓
	8	999 8		220	999 9 ✓
	9	999 8		1	999 8 ✓
4/6	190	999 8	5/11	2	999 8 ✓
	1	999 9		3	999 8 ✓
4/7	2	999 9		4	999 8 ✓

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1942			1942		
5/11	225	999 9	7/2	1	999 9 ✓
	6	999 8		2	999 9 ✓
	7	999 8	End of July	3	999 9 ✓
5/12	8	999 8	8/3	4	999 9 ✓
	9	999 8		5	999 9 ✓
	230	999 8		6	999 9 ✓
5/15	1	999 8	8/5	7	999 9 ✓
	2	999 8		8	999 9 ✓
	3	999 8		9	999 9 ✓
5/19	4	999 9	8/11	10	999 9 ✓
	5	999 9		1	999 9 ✓
	6	999 9		2	999 9 ✓
5/25	7	999 8		3	999 9 ✓
	8	999 9		4	999 9 ✓
	9	999 9		5	999 9 ✓
5/26	240	999 8	8/18	6	999 9 ✓
	1	999 9		7	999 9 ✓
End. May. 1942	2	999 8		8	999 8 ✓
				9	999 9 ✓
				20	999 9 ✓
				1	999 9 ✓
			8/25	2	999 9 ✓
				3	999 9 ✓
				4	999 9 ✓
			8/26	5	999 9 ✓
				6	999 9 ✓
				7	999 9 ✓
				8	999 9 ✓
				9	999 9 ✓
			End of Aug	30	999 9 ✓
			9/2	1	999 9 ✓
				2	999 9 ✓

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2331

DATE.	No. OF MELT.		FINESS.	DATE.	No. OF MELT.	FINESS.	
1942				1942			
8/14	533	<i>Remain</i>	999 8	9/11	43	999 9	/
	4		999 8		4	999 9	/
	5		999 7		5	999 9	/
	6		999 8	9/15	6	999 9	/
8/17	7		999 8		7	999 9	/
	8		999 7		8	999 9	/
	9		999 8	9/17	9	999 9	/
	540		999 8		50	999 9	/
	1		999 7		1	999 9	/
	2		999 8	9/21	2	999 9	/
	3		999 7		3	999 9	/
	4		999 8		4	999 9	/
	5		999 8	9/23	5	999 9	/
	6		999 8		6	999 9	/
	7		999 7		7	999 9	/
8/21	8		999 8	9/28	8	999 9	/
	9		999 8		9	999 9	/
	550		999 8	10/10	60	999 9	/
8/25	1		999 8	9/29	1	999 9	/
	2		999 8		2	999 9	/
	3		999 8		3	999 9	/
	4		999 8	10/6	4	999 9	/
9/1	33		999 9		5	999 9	/
	4		999 9		6	999 9	/
	5		999 9		7	999 9	/
	6		999 9		8	999 8	/
9/9	7		999 9		9	999 8	/
	8		999 9	10/9	70	999 9	/
	9		999 9		1	999 9	/
9/10	40		999 9		2	999 9	/
	1		999 9	10/14	3	999 9	/
	2		999 9		4	999 9	/

ASSAYER'S REGISTER OF MINT FINE GOLD.

9-2221

DATE.	NO. OF MELT.	FINENESS.	DATE.	NO. OF MELT.	FINENESS.
1942			1942		
10/14	75	999 9 ✓	11/18	107	999 9 ✓
	76	999 9 ✓		8	999 9 ✓
	77	999 9 ✓	11/24	9	999 9 ✓
	78	999 9 ✓		110	999 8 ✓
10/20	79	999 9 ✓		1	999 9 ✓
	80	999 9 ✓		2	999 9 ✓
	81	999 9 ✓		3	999 9 ✓
10/21	2	999 9 ✓	Found 3 New	4	999 9 ✓
	3	999 9 ✓	11/30	5	999 9 ✓
	4	999 9 ✓		6	999 9 ✓
10/26	5	999 8 ✓		7	999 9 ✓
	6	999 8 ✓		8	999 8 ✓
	7	999 9 ✓		9	999 9 ✓
10/28	8	999 9 ✓	12/2	120	999 9 ✓
	9	999 8 ✓		1	999 8 ✓
6.58 0.5 →	90	999 9 ✓		2	999 9 ✓
11/4	1	999 9 ✓		3	999 9 ✓
	2	999 8 ✓	12/8	4	999 9 ✓
	3	999 8 ✓		5	999 9 ✓
	4	999 9 ✓		6	999 9 ✓
	5	999 8 ✓	12/8	7	999 8 ✓
	6	999 9 ✓		8	999 8 ✓
11/7	7	999 8 ✓		9	999 8 ✓
	8	999 8 ✓	11/14	130	999 8 ✓
	9	999 8 ✓		1	999 9 ✓
11/11	100	999 8 ✓		2	999 8 ✓
	1	999 8 ✓	12/15	3	999 8 ✓
	2	999 8 ✓		4	999 8 ✓
11/16	3	999 9 ✓		5	999 9 ✓
	4	999 9 ✓	12/23	6	999 9 ✓
	5	999 9 ✓		7	999 9 ✓
11/18	6	999 9 ✓		8	999 9 ✓

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1942			1943		
12/23/42	139	999 8	1/23	171	999 9
	140	999 9	1/26	2	999 9
	1	999 9		3	999 9
12/24	2	999 8	End of JAN		999 9
	3	999 8	1/1	5	999 9
Last No on Dec	4	999 9		6	999 9
12/31	5	999 9		7	999 9
	6	999 9	1/2	8	999 9
	7	999 8		9	999 9
1/2/43	8	999 9		180	999 9
	9	999 8	1/5	1	999 9
	150	999 8		2	999 9
1/6/43	1	999 9		3	999 9
	2	999 8	1/9	4	999 9
	3	999 9		5	999 9
1/8/43	4	999 9		6	999 9
	5	999 9	1/12	7	999 8
	6	999 9		8	999 9
1/9/43	7	999 9		9	999 8
	8	999 9	1/17	190	999 9
	9	999 9		1	999 9
1/14	160	999 9		2	999 8
	1	999 9	1/18	3	999 8
	2	999 9		4	999 9
1/19	3	999 9		5	999 9
	4	999 9	1/25	6	999 9
	5	999 9		7	999 9
1/20	6	999 9		8	999 9
	7	999 9		9	999 9
	8	999 9	200		999 9
1/23	9	999 9	End of Feb		999 9
	170	999 8			

ASSAYER'S REGISTER OF MINT FINE GOLD.

9-2021

DATE. 1943	No. OF MELT.	FINENESS.	DATE.	No. OF MELT.	FINENESS.
3/1	202	999 8 ✓			
	203	999 8 ✓			
	204	999 9 ✓			
3/5	205	999 9 ✓			
	6	999 9 ✓			
	7	999 9 ✓			
	8	999 9 ✓			
	9	999 9 ✓			
	210	999 9 ✓			
3/11	1	999 9 ✓			
	2	999 9 ✓			
	3	999 8 ✓			
3/12	4	999 9 ✓			
	5	999 9 ✓			
	6	999 9 ✓			
3/16	7	999 9 ✓			
	8	999 9 ✓			
	9	999 9 ✓			
3/18	220	999 9 ✓			
	1	999 9 ✓			
	2	999 8 ✓			
3/22	3	999 9 ✓			
	4	999 9 ✓			
	5	999 9 ✓			
3/24	6	999 9 ✓			
	7	999 9 ✓			

End of March
Springing fine

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2231

DATE	NO. OF MELT.	FINESS.	DATE	NO. OF MELT.	FINESS.
1943			1943		
7/23	1	999 9	8/26	33	999 9
	2	999 9		4	999 9
	3	999 9		5	999 9
7/24	4	999 9	→ End of Aug →	6	999 9
End of July	5	999 8	8/28	7	999 8
	6	999 9		8	999 8
7/29	7	999 8		9	999 8
	8	999 9	8/31	40	999 9
	9	999 8		1	999 8
	10	999 9		2	999 8
	1	999 9	9/6	3	999 8
	2	999 9		4	999 9
8/3	3	999 9		5	999 8
	4	999 9	9/10	6	999 8
	5	999 9		7	999 8
8/6	6	999 9		8	999 9
	7	999 9	9/11	9	999 8
	8	999 9		50	999 8
8/8	9	999 9		1	999 8
	20	999 9	9/14	2	999 9
	1	999 9		3	999 8
8/12	2	999 9		4	999 9
	3	999 9	9/16	5	999 9
	4	999 9		6	999 9
8/17	5	999 9		7	999 8
	6	999 9	9/21	8	999 9
	7	999 9		9	999 8
8/20	8	999 9		60	999 9
	9	999 9	9/22	1	999 9
	30	999 9		2	999 9
8/26	1	999 9	← End of Sept →	3	999 9
	2	999 9	9/28	4	999 9

ASSAYER'S REGISTER OF MINT FINE GOLD.

231

DATE. 1943	NO. OF MELT.	FINESS.	DATE.	NO. OF MELT.	FINESS.
9/28	65	999 9	11/1	97	999 9
	66	999 8		8	999 9
	7	999 9		9	999 9
10/1	8	999 9	11/4	100	999 9
	9	999 9		1	999 8
10/6	70	999 9		2	999 9
	1	999 8	11/11	3	999 9
	2	999 9		4	999 9
10/7	3	999 9		5	999 9
	4	999 9	11/16	6	999 9
	5	999 8		7	999 9
10/11	6	999 9		8	999 9
	7	999 9	11/17	9	999 9
	8	999 9		110	999 9
10/14	9	999 9		1	999 9
	80	999 9	11/19	2	999 9
	81	999 9		3	999 9
10/16	2	999 9		4	999 9
	3	999 8	11/20	5	999 9
	4	999 9		6	999 9
10/19	5	999 9		7	999 9
	6	999 9	11/25	8	999 9
	7	999 9		9	999 9
10/25	8	999 9		120	999 9
	9	999 8	11/27	1	999 9
	90	999 8		2	999 9
	1	999 8		3	999 9
	2	999 8	12/2	4	999 9
	3	999 8		5	999 9
10/29	4	999 9		6	999 9
	5	999 9	12/3	7	999 9
	6	999 8		8	999 9

End of

No 1

End of Oct →

ASSAYER'S REGISTER OF MINT FINE GOLD.

9-2231

DATE. 1943	No. OF MELT.	FINENESS.	DATE. 1944	No. OF MELT.	FINENESS.
12/3	129	999 9	1/10	161	999 8
12/7	130	999 9	1/11	2	999 9
	1	999 9		3	999 9
	2	999 9		4	999 9
12/10	3	999 9		5	999 9
	4	999 9	1/17	6	999 9
	5	999 9		7	999 9
12/11	6	999 8		8	999 9
	7	999 9	1/20	9	999 9
	8	999 8		170	999 9
12/18	9	999 9		1	999 9
	140	999 9	1/22	2	999 9
	1	999 9		3	999 9
12/24	2	999 9		4	999 9
	3	999 9	1/26	5	999 9
	4	999 9		6	999 8
	5	999 9		7	999 9
	6	999 9	1/28	8	999 9
	7	999 9		9	999 9
12/30	8	999 9		180	999 9
	9	999 9	2/1	1	999 9
	150	999 9		2	999 9
	1	999 9		3	999 9
	2	999 9	2/5	4	999 9
	3	999 9		5	999 9
1/4/44	4	999 9	2/9	6	999 8
	5	999 9		7	999 9
	6	999 8		8	999 8
	7	999 9		9	999 8
	8	999 9	2/11	190	999 9
	9	999 9		1	999 8
1/10/44	160	999 9		2	999 8

End of

End of

Jan

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2231

DATE. 1944	NO. OF MELT.	FINESS.	DATE. 1944	NO. OF MELT.	FINESS.
2/15	193	999 9	3/8	224	999 9
	4	999 9		5	999 9
	5	999 9	3/20	6	999 9
2/17	6	999 9		7	999 9
	7	999 9		8	999 8
	8	999 9	3/23	9	999 9
2/22	9	999 9		230	999 9
	200	999 9		1	999 9
	1	999 9	3/27	2	999 9
2/23	2	999 9		3	999 9
	3	999 8	End of	4	999 9
End of Feb	4	999 8	3/30	5	999 9
2/28	5	999 9		6	999 9
	6	999 8		7	999 9
	7	999 9	3/31	8	999 9
2/29	8	999 9		9	999 9
	9	999 9		240	999 9
	210	999 9	4/6	1	999 9
3/1	1	999 9		2	999 9
	2	999 9		3	999 9
	3	999 9	4/7	4	999 9
3/7	4	999 9		5	999 9
	5	999 9		6	999 9
	6	999 9	4/12	7	999 9
3/13	7	999 9		8	999 9
	8	999 9		9	999 9
	9	999 9	4/5	250	999 9
3/14	220	999 9		1	999 9
	1	999 9		2	999 9
	2	999 9	4/18	3	999 9
3/18	3	999 9		4	999 9
				5	999 9

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	NO. OF MELT.	FINESS.	DATE.	NO. OF MELT.	FINESS.
1944			1944		
4/24	256	999 9	8/16	1	999 9
	7	999 9		2	999 9
	8	999 9		3	999 9
4/26	9	999 9	8/22	4	999 9
	260	999 9		5	999 9
End of Apr	1	999 8		6	999 9
4/28	2	999 8	8/25	7	999 9
	3	999 8		8	999 9
	4	999 9		9	999 9
4/29	5	999 8	8/28	10	999 9
	6	999 8		1	999 9
	7	999 8		2	999 9
5/6	8	999 9	9/1	3	999 9
	9	999 9		4	999 9
	270	999 9		5	999 9
5/9	1	999 8	9/8	6	999 9
	2	999 8		7	999 9
	3	999 8		8	999 9
5/15	4	999 8	9/12	9	999 9
	5	999 8		20	999 9
	6	999 9		1	999 9
5/17	7	999 8	9/15	2	999 9
	8	999 9		3	999 9
	9	999 8		4	999 9
End of May	280	999 8	9/21	5	999 9
				6	999 9
				7	999 9
			9/25	8	999 9
				9	999 9
			End of	30	999 9
				1	999 9
			9/29	2	999 9

ASSAYER'S REGISTER OF MINT FINE GOLD.

9-2231

DATE.	NO. OF MELT.		FINESS.	DATE.	NO. OF MELT.		FINESS.
1944				1944			
9/29	33		999 9	11/7	64		999 8
10/2	4		999 9		5		999 9
	5		999 9		6		999 9
	6		999 9	11/22	7		999 9
10/7	7		999 9		8		999 9
	8		999 9	End	9		999 9
	9		999 9	11/30	70	43'9	999 9
10/13	40	41 ✓	999 9		1		999 9
	1		999 9		2		999 9
	2		999 9		3		999 8
10/17	3		999 9		4		999 9
	4		999 8		5		999 9
	5		999 9	12/4	6		999 9
10/21	6		999 9		7		999 8
	7		999 9		8		999 9
	8		999 9	12/8	9		999 9
10/24	9		999 9		80	49'8	999 9
	50	42' ✓	999 9		1		999 9
End of	1	Oct	999 9	12/11	2		999 9
10/30	2		999 9		3		999 9
	3		999 9		4		999 9
	4		999 9	12/18	5		999 8
11/3	5		999 9		6		999 8
	6		999 9		7		999 8
	7		999 8	12/21	8		999 8
11/9	8		999 9		9		999 8
	9		999 9		90	40'8	999 8
	60	40' ✓	999 9	12/23	1		999 8
11/11	1		999 9		2		999 8
	2		999 9	End	3		999 8
	3		999 9	11/45	4		999 9

ASSAYER'S REGISTER OF MINT FINE GOLD.

9-2231

DATE.	NO. OF MELT.		FINESS.	DATE.	NO. OF MELT.		FINESS.
1945							
1/1	95		999 9	2/16	127		999 9
	6		999 9		8		999 9
1/3	7		999 9		9		999 9
	8		999 9	2/23	130	.55 8	999 8
	9		999 9		1		999 8
1/6	100	.44 9	999 9		2		999 8
	1		999 9	2/28	3		999 9
	2		999 9		4		999 8
1/11	3		999 9		5		999 9
	4		999 9	3/2	6		999 9
1-15-45	5		999 9		7		999 8
1/16	6		999 9		8		999 8
	7		999 9	3/6	9		999 8
	8		999 8		140	.38 8	999 8
1/23	9		999 9		1		999 8
	110	.44 9	999 9	3/12	2		999 8
	1		999 9		3		999 8
1/25	2		999 9		4		999 8
	3		999 9	3/14	5		999 8
	4		999 9		6		999 8
1/30	5		999 9		7		999 9
	6		999 8	3/16	8		999 8
	7		999 8		9		999 8
Jan	8		999 9		150	.42 8	999 8
2/5	9		999 9	3/23	1		999 8
	120	.44 8	999 8		2		999 8
2/10	1		999 9		3		999 8
	2		999 9	3/29	4		999 8
	3		999 9		5		999 8
2/14	4		999 9		6		999 8
	5		999 8	4/4	7		999 8
	6		999 9		8		999 8

Feb

March

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	No. OF MELT.		FINESS.	DATE.	No. OF MELT.	FINESS.
1945				1945		
4/4	159		9998	11/6	1	9998
4/10	160	44' .8	9998		2	9998
	1		9998		3	9998
	2		9999	11/15	4	9998
4/18	3		9999		5	9998
	4		9999		6	9999
	5		9998		7	9999
	6		9998		8	9998
	7		9998		9	9998
	8		9998	11/23	10	40' .8 9998
4/27	9		9998		1	9999
	170	42' .8	9998		2	9999
	1		9999	11/30	3	9998
	2		9998		4	9998
	3		9998		5	9998
	4		9998		6	9998
	5		9998		7	9998
	6		9997		8	9998
	7		9997		9	9999
April				End Nov	20	54' .8 9999
				12/7	1	9998
					2	9998
					3	9998
				12/12	4	9998
					5	9999
					6	9998
					7	9999
				12/18	8	9998
					9	9998
					30	41' .8 9998
					1	9999
					2	9999

—End 1945—

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	No. OF MELT.	FINENESS.	DATE.	No. OF MELT.	FINENESS.
1945			1946		
12/8	33	999 9	2/6	64	999 8
	34	999 8		65	999 9
	35	999 8		66	999 9
<u>End Dec</u>	36	999 8	2/11	67	999 8
12/28	37	999 9		68	999 9
	38	999 9		69	999 8
	39	999 9	2/15	70	999 9
1/4/46	40	999 9		71	999 8
	41	999 9		72	999 9
	42	999 9	2/21	73	999 9
1/8/46	43	999 9		74	999 9
	44	999 8		75	999 8
	45	999 9		76	999 9
1/9/46	46	999 9		77	999 8
	47	999 9		78	999 9
	48	999 8	2/28	79	999 8
1/16/46	49	999 9		80	999 9
	50	999 9		81	999 8
	51	999 9	3/1	82	999 9
1/18/46	52	999 9		83	999 8
	53	999 9		84	999 9
	54	999 9		85	999 9
1/23/46	55	999 9		86	999 9
	56	999 9		87	999 9
	57	999 8	3/11	88	999 9
	58	999 8		89	999 9
	59	999 9		90	999 9
	60	999 8		91	999 9
1/31/46	61	999 9		92	999 9
	62	999 8		93	999 9
<u>End Jan</u>	63	999 9	3/5	94	999 9

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-231

DATE.	No. OF MELT.	FINENESS.	DATE.	No. OF MELT.	FINENESS.
1946			1946		
3/15	95	999 9	4/1	127	999 8
	96	999 9		128	999 8
3/19	97	999 8		129	999 9
	98	999 8	4/2	130	0.498 999 8
	99	999 8		131	999 9
3/22	100	999 9		132	999 8
6/10/46 sample 10-100	101	999 9	4/26	133	999 8
Letter from Mr. Marshall says these have been received from Bureau of Standards	102	999 9		134	999 8
	103	999 9		135	999 8
	104	999 9	4/30	136	999 8
	105	999 9		137	999 8
	106	999 9	End April	138	999 8
	107	999 8	5/2	139	999 8
	108	999 9		140	0.49 8 999 8
	109	999 9		141	999 8
End March	110	999 9	5/3	142	999 8
4/2	111	999 8		143	999 8
	112	999 9		144	999 8
	113	999 8	5/6	145	999 9
	114	999 8		146	999 8
4/3	115	999 8		147	999 9
	116	999 8	5/14	148	999 8
	117	999 8		149	999 8
4/4	118	999 8		150	0.459 999 9
	119	999 8		151	999 9
	120	999 9		152	999 9
	121	999 8	5/15	153	999 9
	122	999 8		154	999 8
	123	999 8		155	899 8
4/15	124	999 9			
	125	999 8	End May 1946		
	126	999 8	End of 1946		

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE	NO. OF MELT.		FINENESS.	DATE	NO. OF MELT.		FINENESS.
1946							
7/31	1		999 9	9/5	33		999 9
	2		999 9		34		999 9
End July	3		999 9		35		999 8
8/9	4		999 8		36		999 9
	5		999 9	9/12	37		999 9
	6		999 8		38		999 9
	7		999 9		39		999 9
	8		999 8	9/13	40	61	999 9
	9		999 9		41		999 9
8/12	10	50	999 9		42		999 9
	11		999 9	9/17	43		999 9
	12		999 9		44		999 8
8/19	13		999 8		45		999 8
	14		999 8	9/19	46		999 9
	15		999 8		47		999 9
	16		999 9		48		999 9
	17		999 8	9/27	49		999 9
8/21	18		999 8		50	40	999 9
	19		999 8		51		999 9
	20	51	999 8		52		999 9
	21		999 8		53		999 9
8/26	22		999 9		54		999 9
	23		999 9	10/2	55		999 9
	24		999 8		56		999 9
8/28	25		999 9		57		999 8
	26		999 9		58		999 9
	27		999 8		59		999 9
8/29	28		999 8		60	51	999 9
	29		999 9	10/9	61		999 8
	30	49	999 9		62		999 8
9/5	31		999 9		63		999 8
	32		999 9		64		999 9

End Sept

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	No. OF MELT.		FINENESS.	DATE.	No. OF MELT.		FINENESS.
1946							
10/9	65		9999	12/6	97		9998
	66		9998		98		9998
10/16	67		9998		99		9999
	68		9998	12/8	100	58'	9998
	69		9999		101		9999
10/18	70	51'	9998		102		9998
	71		9999		103		9998
	72		9998		104		9998
10/22	73		9998		105		9998
	74		9999	12/19	106		9998
	75		9998		107		9999
10/24	76		9999		108		9998
	77		9998	11/23	109		9999
	78		9999		110	50'	9998
10/28	79		9999		111		9998
	80	59'	9998		112		9999
<u>End Oct</u>	81		9999		113		9998
10/31	82		9998		114		9998
	83		9998	11/30	115		9999
	84		9998		116		9998
11/5	85		9999		117		9998
	86		9999		118		9998
	87		9998		119		9998
11/13	88		9998		120	51'	9999
	89		9999	1/3	121		9998
	90	54'	9999		122		9998
11/20	91		9999		123		9999
	92		9998		124		9998
	93		9999		125		9998
	94		9999		126		9998
	95		9999	1/7	127		9998
<u>End Nov</u>	96		9998		128		9998

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2231

DATE.	No. OF MELT.		FINENESS.	DATE.	No. OF MELT.	FINENESS.
1947						
1/8	129		999 9	2/17	161	999 8
1/9	130	41' 8	999 8		162	999 8
	131		999 9	2/27	163	999 8
	132		999 9		164	999 8
1/15	133		999 8		165	999 8
	134		999 8		166	999 8
	135		999 8		167	999 8
	136		999 8	Enl 3/6	168	999 8
	137		999 8	3/4	169	999 9
	138		999 8		170	999 8
1/20	139		999 9		171	999 8
	140	37' 8	999 8		172	999 8
	141		999 8		173	999 8
1/31	142		999 8		174	999 8
	143		999 8	3/6	175	999 8
Enl San	144		999 9		176	999 8
2/3	145		999 8		177	999 8
	146		999 9	3/11	178	999 8
	147		999 8		179	999 8
2/5	148		999 9		180	999 8
	149		999 8		181	999 8
	150	49' 8	999 8		182	999 8
2/11	151		999 9		183	999 8
	152		999 8	3/18	184	999 8
	153		999 8		185	999 8
2/12	154		999 8		186	999 8
	155		999 7		187	999 8
	156		999 8		188	999 8
2/17	157		999 8		189	999 8
	158		999 8	4/1	190	999 8
	159		999 8		191	999 9
	160	54' 8	999 8		192	999 8
						Enl 4/1

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2331

DATE	No. OF MELT.		FINENESS.	DATE.	No. OF MELT.		FINENESS.
1947							
4/3	193		999 8				
	194		999 9				
	195		999 9				
4/14	196		999 8				
	197		999 8				
	198		999 8				
4/17	199		999 8				
	200	51'	8				
	201		999 9				
4/18	202		999 8				
	203		999 8				
	204		999 8				
4/25	205		999 8				
	206		999 7				
	207		999 9				
4/28	208		999 8				
	209		999 8				
End Apr	210	59'	8				
5/2	211		999 8				
	212		999 8				
	213		999 8				
5/6	214		999 8				
	215		999 8				
	216		999 8				
5/8	217		999 8				
	218		999 8				
	219		999 7				
5/12	220	59'	8				
	221		999 8				
	222		999 8				
	223		999 8				
End May	224		999 8				

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2231

DATE.	No. OF MELT.		FINENESS.	DATE.	No. OF MELT.		FINENESS.
1947				1947			
9/3	1		996 6	9/23	33		999 9
	2		996 9	9/26	34		997 1
	3		997 0		35		997 2
9/4	4		996 9		36		997 0
	5		996 7		37		997 0
	6		996 9		38		996 9
9/8	7		996 7		39		997 3
	8		997 2	9/30	40	51	997 2
	9		996 9		41		997 1
9/10	10	51	999 8		42		997 3
	11		999 9	10/2	43		999 9
	12		999 9		44		999 8
9/11	13		997 3		45		999 9
	14		996 8	10/6	46		999 8
	15		997 1		47		999 8
9/12	16		997 4		48		999 8
	17		997 0	10/8	49		999 8
	18		997 2		50	51	999 8
9/17	19		999 9		51		999 9
	20	51	999 8	10/10	52		948 0
	21		999 8		53		997 3
	22		997 0		54		997 5
	23		996 9	10/15	55		999 8
	24		997 0		56		999 9
9/18	25		999 8		57		999 9
	26		999 8	10/23	58		999 9
	27		999 9		59		999 8
9/22	28		996 8		60	48	999 8
	29		997 0	10/31	61		999 9
	30	51	996 9		62		999 9
9/23	31		999 9		63		999 9
	32		999 9				

End Sept

End Oct

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2231

DATE	NO. OF MELT.		FINENESS.	DATE.	NO. OF MELT.		FINENESS.
1947							
"/7	64		999 8	12/19	95		999 9
	65		999 9		96		999 8
	66		999 9		97		999 8
"/10	67		999 8		98		999 9
	68		999 8		99		999 9
	69		999 9	12/29	100	46✓ 9	998 9
	70	41✓ 5	997 5		101		997 5
	71		997 6		102		997 4
	72		997 6	12/31	103		996 8
"/18	73		999 8		104		997 0
	74		999 8	End Dec	105		997 1
	75		999 9	1/4/48	106		999 9
"/26	76		999 9		107		999 9
	77		999 8		108		999 9
	78		999 8	1/8/48	109		999 8
	79		999 8		110	40✓ 9	999 9
	80	50✓ 9	999 9		111		999 8
End Nov	81		999 8	1/9/48	112		999 8
12/3	82		999 9		113		999 8
	83		999 8		114		999 8
	84		999 8	1/2	115		996 8
12/5	85		999 8		116		996 4
	86		999 8		117		997 0
	87		999 8	1/14	118		999 8
12/9	88		999 8		119		999 8
	89		999 8		120	40✓ 8	999 8
	90	50✓ 8	999 8	1/16	121		999 8
12/12	91		999 7		122		999 9
	92		999 8		123		999 8
	93		999 8	1/20	124		999 7
12/19	94		999 9		125		999 8

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2531

DATE. 1948	No. OF MELT.		FINENESS.	DATE. 1948	No. OF MELT.		FINENESS.
1/20	126		999 8	2/5	157		996 1
	127		999 8		158		995 3
	128		999 7		159		995 6
1/23	129		999 8	2/6	160	47 3	995 3
	130	44 8	999 8		161		995 6
	131		999 8		162		995 5
	132		999 8	2/9	163		999 9
	133		999 8		164		999 8
	134		999 7		165		999 8
	135		999 8		166		995 9
1/26	136		996 3		167		996 0
	137		996 0		168		995 9
	138		996 6	2/11	169		995 7
1/28	139		999 8		170	53 4	995 4
	140	47 8	999 8		171		995 5
	141		999 8	2/12	172		995 3
	142		995 9		173		995 3
	143		996 4		174		995 7
End Jan	144		996 1		175		995 5
1/30	145		999 8		176		995 4
	146		999 8		177		995 4
	147		999 7	2/9	178		995 3
2/3	148		999 7		179		995 4
	149		999 8		180	47 4	995 3
	150	48 8	999 8	2/11	181		999 9
	151		996 0		182		999 9
	152		995 9		183		999 9
	153		996 3	2/9	184		995 6
2/4	154		996 1		185		995 6
	155		995 9		186		995 6
	156		995 4		187		995 2

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2291

DATE. 1948	No. OF MELT.		FINESS.	DATE. 1948	No. OF MELT.		FINESS.
2/19	188		995 2	3/2	219		997 5
	189		996 7	3/3	220	471 5	997 5
2/20	190	541 4	997 4		221		997 4
	191		997 5		222		997 4
	192		997 5	3/4	223		997 6
2/24	193		997 5		224		997 5
	194		997 7		225		997 5
	195		997 2	3/5	226		997 5
2/25	196		997 7		227		997 5
	197		996 4		228		997 5
	198		996 2		229		999 8
2/27	199		997 4		230	431 8	999 8
	200	541 0	997 0		231		999 8
	201		997 7		232		999 8
	202		997 6		233		999 9
	203		997 8		234		999 9
	204		997 5	3/19	235		997 6
	205		997 6		236		997 4
	206		997 6		237		999 7
	207		997 7				
2/16	208		999 7	1949 3/30	1		999 9
	209		999 9		2		999 9
End Feb	210	521 8	999 8	9/15	3		999 9
3/1	211		997 7		4		999 8
	212		997 7	9/20	5		999 8
	213		997 7	9/21	6		999 7
	214		997 7		7		999 9
	215		997 7		8		999 8
	216		997 2	9/23	9		999 9
3/2	217		997 5		10	461 9	999 9
	218		997 3	9/26	11		999 9
					12		999 9

Was Ref x 345

END Fiscal 1948

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2591

DATE 1949	NO. OF MELT.		FINESS.	DATE 1949	NO. OF MELT.		FINESS.
Sept 9/27	13		999 9	12/8	45		999 9
9/28	14		999 9		46		999 9
10/5	15		999 9		47		999 9
10/2	16		999 9	12/2	48		999 9
	17		999 9		49		999 9
10/13	18		999 9		50	41 1/2 9	999 9
	19		999 9		51		997 5
	20	46 1/2 9	999 9		52		996 9
10/20	21		999 9	12/9	53		997 4
	22		999 9		54		997 6
10/27	23		999 9	12/21	55		999 9
Oct 24	24		999 9		56		999 9
11/1	25		999 9		57		999 9
	26		999 9	12/27	58		999 9
11/3	27		999 9		59		999 9
	28		999 9	Dec 60	42 1/2 9		999 9
11/4	29		999 9	12/29	61		999 9
	30	38 1/2 8	999 8		62		999 9
11/6	31		999 9	1/4/50	63		999 9
	32		999 9		64		999 9
11/7	33		999 9	1/6	65		999 9
	34		999 9		66		999 9
	35		999 9		67		997 6
11/21	36		999 9		68		997 6
	37		999 9	1/9	69		999 9
	38		999 9		70	43 1/2 9	999 9
Nov 39	39		999 9	1/11	71		999 9
12/2	40	42 1/2 6	999 6		72		999 9
	41		999 8	1/12	73		999 9
	42		999 8		74		999 9
12/6	43		999 9	1/16	75		997 6
	44		999 9		76		997 8

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE. 1950	No. OF MELT.	FINENESS.	DATE. 1950	No. OF MELT.	FINENESS.
1/17	77	997 4	3/23	108	999 9 ✓
	78	997 4	3/29	109	999 9 ✓
	79	997 7		110	999 9 ✓
1/19	80 40. 5	997 5		111	999 9 ✓
	81	997 7	3/30	112	999 9 ✓
	82	997 7		113	999 8 ✓
1/23	83	997 5		114	999 9 ✓
	84	997 9	Mar	115	999 9 ✓
	85	999 8			
	86	999 8			
1/25	87	999 9			
	88	999 9			
	89	999 9			
	90 40. 9	999 9			
1/30	91	999 9			
	92	996 5			
	93	998 3			
1/31	94	999 9			
Jan	95	999 9			
2/5	96	999 9			
	97	999 9			
2/28	98	999 9			
	99	999 9			
	100 41. 9	999 9			
Feb	101	999 9			
3/2	102	999 9			
3/9	103	999 9			
	104	999 9			
3/10	105	999 9			
3/17	106	999 9			
3/23	107	999 9			

ASSAYER'S REGISTER OF MINT FINE GOLD.

Fiscal year 1951

DATE	NO. OF MELT.	FINESS.	DATE 1950	NO. OF MELT.	FINESS.
1950					
8/18	1	9976	9/4	33	9980
	2	9982		4	9981
	3	9977		5	9980
	4	9983		6	9979
	5	9978		7	9982
8/21	6	9982		8	9985
	7	9981	9/5	9	9980
	8	9982		40	9979
	9	9984		1	9979
8/21	10	9985		2	9980
	11	9985		3	9976
	12	9982	9/9	4	9978
	13	9982		5	9977
	14	9984		6	9978
	15	9979		7	9976
	16	9983		8	9974
	17	9983		9	9981
	18	9982		50	9976
	19	9982		1	9978
8/31	20	9981	9/21	2	9980
	1	9984		3	9982
	2	9981		4	9983
	3	9980		5	9982
	4	9981		6	9982
	5	9981	9/22	7	9984
	6	9982		8	9985
	7	9982		9	9983
9/1	8	9980	9/25	60	9982
	9	9981		1	9981
9/13	30	9979	9/27	2	9984
	1	9980		3	9982
	2	9980		4	9985

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	No. OF		FINESS.	DATE.	No. OF		FINESS.
1950	MELT.			1950	MELT.		
9/27	65		998 3	10/12	97		997 7
	6		998 3		98		997 9
	7		998 4	10/13	99		997 2
9/28	8		998 5		100	47 7	997 7
	9		998 2		1		997 7
9/29	70	47 2	997 8		2		998 0
	1		998 4		3		997 8
	2		998 0		4		997 7
10/3 <i>Sept</i>	3		998 0	10/17	5		998 0
	4		997 9		6		998 0
	5		998 0		7		997 8
	6		997 6		8		997 8
10/4	7		998 1		9		998 4
	8		997 5				<i>est</i>
	9		997 9				
10/5	80	40 2	997 7				
	1		997 7				
	2		997 5				
	3		997 8				
	4		997 5				
	5		997 7				
10/6	6		997 7				
10/9	7		997 7				
	8		997 7				
	9		997 6				
	90	49 2	997 5				
10/10	1		997 6				
	2		998 1				
	3		997 9				
10/12	4		997 9				
	5		997 5				
	6		997 7				

Fiscal Year 1952

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-9221

DATE.	No. OF MELT.		FINESS.	DATE.	No. OF MELT.	FINESS.
1952				1952		
4/14	1		999 1	5/2	33	998 2
	2		998 4		34	998 5
4/15	3		998 5		35	998 5
	4		998 7		36	998 3
	5		998 4		37	998 4
4/18	6		997 7		38	998 3
	7		998 9	5/5	39	998 5
	8		998 4		40	998 7
4/21	9		998 2		41	998 4
	10	42	998 5		42	998 7
	1		998 7			
	2		998 3			
	3		998 6			
	4		998 3			
	5		998 3			
4/22	6		999 0			
	7		998 6			
	8		998 1			
	9		998 0			
	20	40	998 6			
4/25	1		997 9			
	2		997 9			
	3		998 0			
	4		998 2			
	5		997 6			
	6		998 2			
4/28	7		998 1			
	8		998 3			
	9		998 3			
4/29	30	50	998 5			
	31		998 5			
	32		998 3			

Fiscal Year 1953

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE 1952	No. OF MELT.	FINESS.	DATE 1952	No. OF MELT.	FINESS.
10/13	1	9998	10/13	32	9977
	2	9998		3	9982
	3	9999		4	9983
	4	9998	10/14	5	9982
10/16	5	9998		6	9978
	6	9996	10/16	7	9981
10/22	7	9997		8	9977
	8	9999		9	9980
	9	9998		40	9981
	10	9998		1	9981
10/23	1	9997		2	9986
	2	9997	10/23	3	9993
	3	9998		4	9994
	4	9997		5	9993
10/27	5	9005	10/27	6	9996
	6	8997		7	9994
	7	8998		8	9996
10/28	8	8999		9	9999
	9	8999		50	9999
	20	8998	10/28	1	9998
10/29	1	8997		2	9999
	2	8998		3	9998
10/30	3	8999	10/30	4	9999
	4	8997		5	9999
	5	8998		6	9999
	6	9980		7	9998
	7	9980	10/30	8	9998
	8	9983		9	9995
10/31	9	9982	10/31	60	9995
	30	9985		1	9995
	1	9980		2	9983
				3	9984

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	No. OF MELT.	FINENESS.	DATE.	No. OF MELT.	FINENESS.
1952			1952	1953	
12/26	64	998 4	12/29	96	999 9
	5	998 4		7	999 9
12/3	6	998 3		8	999 9
	7	998 4	12/22	9	999 8
	8	998 1	1953	100 55	999 9
12/5	9	998 4	12/23	1	999 8
	70	998 7		2	999 9
12/9	1	998 4	2/5	3	999 9
	2	998 4	2/6	4	999 9
12/10	3	998 4	2/5	5	999 9
	4	997 9	2	6	999 9
	5	998 1		7	999 9
	6	998 5		8	999 9
12/11	7	998 1	2/6	9	999 9
	8	998 1		11 0	999 9
	9	997 9	2/5	1	999 9
	80	999 9		2	999 9
	1	999 9		3	999 9
	2	999 8		4	999 9
12/16	3	999 8		5	999 9
	4	999 9	12/6	6	999 9
	5	999 8			
	6	999 8			
	7	999 9			
12/18	8	999 8			
	9	999 8			
	90	998 6			
	1	998 2			
	2	998 2			
	3	998 0			
12/19	4	998 1			
	5	998 0			

Fiscal Year 1954

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2551

DATE.	No. OF MELT.	FINENESS.	DATE.	No. OF MELT.	FINENESS.
1953			1953		
8/12	500	999 8	9/24	531	998 0
	1	999 8		2	998 7
	2	999 8	9/29	3	997 9
	3	999 7	10/5	4	998 2
	4	998 2		5	998 2
8/13	5	998 5		6	999 4
	6	998 7		7	999 4
8/14	7	998 3	10/6	8	998 3
8/20	8	998 3	10/9	9	998 1
	9	998 2		540	998 6
8/24	510	998 0	10/12	1	999 7
	1	999 7		2	999 7
	2	999 6		3	997 6
8/27	3	998 3	10/16	4	998 1
	4	998 8		5	997 3
8/28	5	998 4		6	997 6
9/4	6	998 4		7	998 8
	7	998 4	10/22	8	997 9
	8	999 7		9	998 5
	9	999 8	10/26	550	999 7
9/10	520	997 8		1	999 6
	1	999 8		2	998 0
	2	999 8	10/29	3	998 2
9/14	3	998 0		4	998 3
	4	998 4		5	998 2
	5	997 4	11/6	6	997 0
	6	997 4		7	997 9
9/21	7	998 0		8	999 8
	8	998 8		9	999 8
	9	999 7		560	999 9
	530	998 0	11/9	1	999 9

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	NO. OF MELT.	FINESS.	DATE.	NO. OF MELT.	FINESS.
1953			1954		
11/9	562	9975	11/7	594	9998
11/12	3	9989	5		9997
	4	9979	11/11	6	9998
11/16	5	9978	7		9997
11/20	6	9980	8		9982
	7	9988	11/13	9	9981
	8	9998	600		9984
	9	9997	11/14	1	9980
11/23	570	9980	11/20	2	9976
11/27	1	9978	3		9982
	2	9984	11/22	4	9998
11/30	3	9997	5		9997
	4	9996	6		9975
	5	9967	11/27	7	9978
12/2	6	9981	8		9985
	7	9979	11/29	9	9998
12/4	8	9978	610		9997
12/11	9	9981	12/1	1	9982
12/10	580	9984	2/8	2	9973
12/11	1	9977	3		9988
	2	9974	4		9982
12/16	3	9979	5		9980
	4	9983	6		9984
12/18	5	9981	7		9976
12/21	6	9980	8		9980
	7	9987	2/17	9	9979
12/30	8	9980	620		9980
12/31	9	9979	2/19	1	9978
	590	9985	2/23	2	9996
1/5	1	9981	2/24	3	9997
1/7	2	9984	2/1	4	9984
	3	9987	5		9978

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE. 1954	NO. OF MELT.	FINENESS.	DATE. 1954	NO. OF MELT.	FINENESS.
3/1	626	997 6	4/1	657	998 0
3/2	7	999 7		8	998 4
	8	999 7	4/21	9	997 8
	9 sd .6	999 6		660	998 5
3/4	630	998 0		1	999 7
	1	998 4		2	999 8
3/5	2	999 7		3	997 6
	3	999 7		4	998 8
3/8	4	998 3	4/23	5	997 7
3/12	5	997 8	4/28	6	998 1
	6	998 2		7	998 6
	7	997 5	5/3	8	999 7
	8	997 4		9	999 7
3/19	9	998 1		670	998 0
	640	998 7	5/5	1	998 0
	1	999 6		2	998 8
	2	999 7	5/7	3	998 1
	3	997 5	5/11	4	999 7
3/24	4	997 9		5	999 8
	5	998 0	5/12	6	997 8
3/26	6	999 8		7	998 3
	7	999 6	5/13	8	998 7
3/29	8	997 2		9	998 4
4/2	9	997 5		680	998 5
	650	997 7		1	997 8
	1	997 5	5/20	2	997 8
4/8	2	997 5		3	998 7
	3	998 2		4	997 4
	4	999 7	5/24	5	999 7
	5	999 6	5/25	6	999 7
	6	997 6		7	999 6

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	NO. OF MELT.		FINENESS.	DATE.	NO. OF MELT.	FINENESS.
1954						
5/27	688		9980			
	9	52	9985			
	690	5	9982			
6/2	1		9978			
	2		9983			
6/3	3		9998			
	4		9998			
6/7	5		9983			
	6		9998			
	7		9998			
6/9	8		9980			
	9	45	9975			
6/10	700	5	9981			
6/15	1		9983			
	2		9977			
	3		9984			
6/16	4		9980			

Fiscal Year 1955

Deposit Melt Room Production

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-221

DATE. 1954	NO. OF MELT.	FINENESS.	DATE. 1954	NO. OF MELT.	FINENESS.
6/28	500	998 0	8/6	532	997 7
	1	998 2	8/11	3	997 7
	2	997 6		4	998 0
	3	999 9	8/13	5	997 3
	4	999 8		6	998 1
6/30	5	997 8		7	998 0
	6	998 7	8/17	8	998 6
7/1	7	999 8		9	999 0
	8	999 8	8/19	540	998 2
7/6	9	997 8	8/25	1	999 8
7/8	510	998 0		2	999 7
	1	998 0	8/26	3	997 8
	2	997 3		4	997 9
7/12	3	999 7	8/31	5	997 2
	4	999 7	9/1	6	998 0
7/13	5	998 3		7	997 9
	6	998 5	9/3	8	997 5
	7	998 5	9/9	9	999 7
7/15	8	998 9		550	999 7
	9	997 4		1	997 4
7/21	520	998 2		2	998 2
	1	998 5	9/10	3	997 9
7/22	2	999 8	9/14	4	998 1
	3	998 2		5	998 5
7/28	4	998 2		6	998 3
	5	998 7		7	998 5
7/29	6	997 6	9/16	8	998 2
8/2	7	999 9		9	999 7
8/4	8	997 1	9/17	560	999 8
	9	998 3	9/23	1	997 9
8/5	530	999 9		2	998 6
	1	999 8		3	997 7

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	NO. OF MELT.		FINESS.	DATE.	NO. OF MELT.	FINESS.
1954				1954		
9/28	564		998 5 ✓	11/1	595	999 8 ✓
	5		997 9 ✓	11/23	596	996 4 ✓
10/1	6		997 9 ✓	11/24	7	995 9 ✓
10/6	7		997 6 ✓		8	997 8 ✓
	8		998 1 ✓	11/26	9 52	999 7 ✓
10/8	9	55 9	997 9 ✓		600	999 8 ✓
10/13	570		998 3 ✓		1	997 3 ✓
	1		997 2 ✓	12/1	2	997 5 ✓
	2		997 2 ✓		3	997 9 ✓
	3		997 8 ✓	12/3	4	997 2 ✓
10/14	4		998 0 ✓	12/9	5	997 8 ✓
10/20	5		997 5 ✓	12/9	6	998 3 ✓
	6		998 7 ✓		7	997 3 ✓
10/21	7		997 5 ✓	12/15	8	998 1 ✓
	8		997 5 ✓		9 56	997 7 ✓
11/27	9	55 5	998 5 ✓		610	998 5 ✓
11/2	580		997 1 ✓	12/17	1	997 5 ✓
11/3	1		999 8 ✓	12/22	2	998 2 ✓
	2		999 8 ✓		3	997 2 ✓
11/4	3		998 1 ✓	12/27	4	997 3 ✓
	4		997 2 ✓	12/30	5	997 8 ✓
11/9	5		997 2 ✓		6	997 8 ✓
	6		999 7 ✓	1/3/55	7	997 5 ✓
	7		999 7 ✓	1/5	8	997 7 ✓
	8		997 5 ✓		9 44	997 1 ✓
	9	49 2	998 2 ✓	1/6	620	998 0 ✓
11/12	590		997 4 ✓	1/12	1	997 4 ✓
	1		998 6 ✓		2	998 2 ✓
11/17	2		997 5 ✓	1/14	3	995 6 ✓
	3		997 9 ✓	1/20	4	997 3 ✓
	4		999 7 ✓		5	998 7 ✓
					6	997 2 ✓

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2231

DATE. 1955	NO. OF MELT.		FINESS.	DATE. 1955	NO. OF MELT.		FINESS.
1/25	627		9969	3/23	658		9982
	8		9981		9 ⁵⁴	8	9998
1/31	9 ⁴⁰	9	9969		660		9998
2/2	630		9980	3/25	1		9977
	1		9981	3/30	2		9971
2/7	2		9983		3		9970
	3		9996	3/31	4		9974
2/8	4		9984	4/6	5		9973
	5		9982		6		9981
2/10	6		9973	4/11	7		9969
2/16	7		9981	4/13	8		9980
	8		9980		9 ⁵¹	9	9979
	9	R.M.	9971	4/14	670		9972
	9 ⁴⁴	5	9975		1		9981
2/17	640		9972	4/20	2		9970
2/24	1		9976		3		9980
	2		9983		4		9998
3/2	3		9970		5		9972
	4		9972	4/26	6		9981
3/3	5		9982		7		9979
	6		9975	4/29	8		9997
3/8	7		9994		9 ⁴⁷	2	9972
	8		9980	5/5	680		9973
	9 ⁴¹	3	9974		1		9982
3/10	650		9973	5/6	2		9979
3/15	1		9976	5/9	3		8997
	2		9973		4		9998
	3		9986	5/11	5		9977
3/17	4		9997		6		9985
	5		9996	5/12	7		9974
	6		9973		8		9980
3/24	7		9963	5/16	9		9982

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2031

DATE.	NO. OF MELT.	FINENESS.	DATE.	NO. OF MELT.	FINENESS.
1955					
5/16	690	999 6			
	1	999 8			
	2	999 7			
5/20	3	998 4			
	4	998 5			
5/23	5	997 9			
5/26	6	997 7			
	7	999 8			
6/3	8	997 7			
	9	998 3			
	700	997 2			
	1	997 7			
	2	998 1			
	3	996 3			
6/8	4	999 4			
	5	997 7			
	6	998 1			
6/15	7	997 4			
	8	997 2			
	9	997 9			
	710	997 4			
6/17	1	997 3			
	2	997 8			

Fiscal Year 1953

Refinery Production

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE 1954	NO. OF MELT.		FINENESS.	DATE 1954	NO. OF MELT.		FINENESS.	
8/30	1		998 0	9/5	33		998 1	/
	2		998 0		4		998 0	/
	3		998 1		5		998 2	/
8/31	4		998 0		6		997 9	/
	5		997 8	9/17	7		998 1	/
	6		998 1		8		997 9	/
9/3	7		998 1		9		997 8	/
	8		999 1		40	51	998 3	/
	9		999 2		1		998 2	/
	10	38	999 0		2		998 2	/
9/7	1		998 9	9/21	3		998 3	/
	2		999 0		4		998 1	/
	3		999 3		5		998 0	/
	4		998 7		6		998 1	/
	5		998 6		7		998 1	/
	6		998 7		8		998 0	/
	7		998 8	9/22	9		998 2	/
9/10	8		999 0		50	49	998 8	/
	9		998 4		1		998 7	/
	20	55	997 9		2		998 5	/
	1		997 8		3		998 2	/
	2		998 1	9/24	4		998 4	/
	3		998 1		5		998 5	/
	4		997 9		6		998 8	/
9/13	5		997 7		7		998 5	/
	6		997 9		8		997 6	/
	7		997 8		9		998 6	/
9/14	8		997 8	9/27	60	44	998 4	/
	9		998 2		1		998 6	/
	30	57	998 0		2		998 8	/
	1		997 7		3		999 0	/
9/15	2		998 0		4		998 8	/

ASSAYER'S REGISTER OF MINT FINE GOLD.

5-2001

DATE.	NO. OF MELT.		FINENESS.	DATE.	NO. OF MELT.	FINENESS.
1954						
9/28	65		998 8 ✓			
	6		998 3 ✓			
	7		998 7 ✓			
	8		998 3 ✓			
	9		998 8 ✓			
	70	49	998 9 ✓			
9/29	1		998 4 ✓			
	2		999 1 ✓			
	3		999 0 ✓			
9/30	4		998 9 ✓			
	5		998 7 ✓			
	6		998 9 ✓			
10/1	7		998 4 ✓			
	8		999 0 ✓			
	9		998 7 ✓			
	80	37	999 1 ✓			
	1		998 7 ✓			
	2		999 1 ✓			
	3		998 8 ✓			
	4		999 0 ✓			
10/8	5		998 7 ✓			
	6		998 3 ✓			
	7		998 3 ✓			
	8		998 8 ✓			
10/11	9		998 2 ✓			
	90	47	995 5 ✓			
	1		998 1 ✓			
	2		998 1 ✓			
	3		998 4 ✓			
	4		998 4 ✓			
10/13	5		998 3 ✓			
	6		998 5 ✓			

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	NO. OF MELT.		FINENESS.	DATE.	NO. OF MELT.		FINENESS.
1954				1954			
10/13	97		999 5	12/7	129		999 8
	98		998 5		130	50	999 7
	99		999 5		1		999 8
	100	42	999 6	12/8	2		999 7
10/15	101		999 9		3		999 8
	2		999 9	12/10	4		999 7
	3		999 9		5		999 8
	4		999 9		6		999 8
	5		999 9		7		999 7
	6		999 9	12/5	8		999 8
10/18	7		999 8		9		999 8
	8		999 8		140	44	999 8
	9		999 8		1		999 8
10/20	110	41	999 6		2		999 8
	1		999 7	1/27	3		999 9
	2		999 8		4		999 8
10/25	3		999 8	1/28	5		999 8
	4		999 8		6		999 8
	5		999 6		7		999 8
	6		999 7	1/31	8		999 9
	7		999 8		9		999 9
10/26	8		999 8		150	45	999 9
	9		999 8		1		999 8
	120	40	999 8		2		999 9
	1		999 7	2/2	3		999 9
12/1	2		999 8		4		999 8
	3		999 8		5		999 9
12/3	4		999 8	2/4	6		999 9
	5		999 8		7		999 9
	6		999 8		8		999 9
12/7	7		999 8		9		999 9
	8		999 8		160	41	999 9

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	NO. OF MELT.	FINENESS.	DATE.	NO. OF MELT.	FINENESS.
1955			1955		
2/8	161	9998	4/18	193	9999
	2	9998		4	9998
3/7	3	9997	4/27	5	9999
	4	9997		6	9999
3/8	5	9998	4/29	7	9998
3/10	6	9999		8	9999
	7	9998	5/1	9	9999
	8	9997	5/4	200	9998
3/14	9	9998		57	8
	170	9997		1	9998
	1	9998		2	9999
	2	9998		3	9999
	3	9999		4	9998
	4	9999		5	9999
	5	9999			
	6	9999			
	7	9999			
	8	9999			
	9	9999			
	180	9999			
4/5	1	9998			
	2	9999			
	3	9998			
	4	9998			
4/6	5	9998			
	6	9999			
4/7	7	9998			
	8	9998			
	9	9998			
4/8	190	9999			
4/15	1	9999			
	2	9999			

Fiscal year 1956

Deposit Melt Room

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE. 1955	No. OF MELT.	FINENESS.	DATE. 1955	No. OF MELT.	FINENESS.
7/1	500	997 6	8/24	532	998 0
	1	997 4		533	998 8
	2	997 6		4	997 7
7/5	3	998 2	8/30	5	997 4
	4	998 1		6	998 6
	5	998 2	9/1	7	997 6
7/11	6	997 8	9/6	8	999 5
	7	997 9	9/8	9	997 8
	8	996 7		540	996 8
	9	999 7	9/9	1	997 2
7/12	510	999 6	9/13	2	998 1
	1	997 7		3	997 5
7/13	2	998 6		4	997 8
7/15	3	997 2		5	998 9
7/19	4	997 9	9/15	6	998 6
	5	998 7	9/21	7	997 9
7/22	6	997 9		8	998 1
7/27	7	997 7	9/22	9	997 9
	8	998 5	9/27	550	998 0
7/28	9	997 5		1	997 5
8/2	520	998 3	9/28	2	997 4
8/3	1	998 4	10/4	3	997 7
8/5	2	997 9		4	998 5
	3	999 4	10/7	5	997 6
	4	997 8	10/11	6	997 5
8/11	5	998 3		7	998 2
	6	997 9	10/14	8	998 3
8/12	7	998 0		9	998 4
	8	998 5		560	997 2
8/17	9	998 4	11/18	1	997 5
	530	999 0		2	996 5
8/18	1	998 1	10/20	3	997 8

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	No. OF MELT.	FINENESS.	DATE.	No. OF MELT.	FINENESS.
1955			1955		
10/25	564	997 6	11/29	596	997 3
	5	997 7	1/5/56	7	997 4
10/27	6	997 8		8	997 9
11/2	7	997 7		9	996 9
	8	998 0	1/11	600	997 3
11/3	9	997 5		1	997 6
11/8	570	997 7	1/13	2	997 0
	1	997 6	1/17	3	997 9
11/14	2	997 8		4	998 0
11/16	3	998 6	1/20	5	996 3
	4	997 8	1/24	6	997 4
	5	998 5	1/25	7	997 0
11/18	6	997 2	1/26	8	997 8
11/23	7	998 0	2/1	9	996 4
11/25	8	997 8		610	997 5
11/25	9	997 8	1/23	1	997 3
11/30	580	997 5	2/7	2	997 1
	1	996 0		3	997 5
12/1	2	997 8	2/9	4	997 5
12/6	3	997 7	2/15	5	997 9
	4	997 8		6	997 6
12/8	5	997 7		7	997 0
12/16	6	997 8		8	996 6
	7	997 8	2/16	9	996 9
	8	998 3	2/27	620	996 9
	9	998 7	2/23	1	997 4
12/21	590	997 5	2/27	2	997 3
	1	997 6	3/1	3	997 4
	2	997 4		4	996 3
12/23	3	997 0		5	996 2
12/28	4	998 0	3/7	6	997 0
	5	997 8		7	997 3

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2311

DATE.	No. OF MELT.			FINENESS.	DATE.	No. OF MELT.			FINENESS.
1956					1956				
3/8	628			997 0	5/17	660			998 7 ✓
3/3	629	49	8	996 7		1			997 9 ✓
	630			997 1		2			995 9 ✓
	1			996 5		3			997 7 ✓
3/15	2			998 2	5/22	4			997 7 ✓
	3			996 8		5			998 2 ✓
3/21	4			997 1	5/28	6			998 0 ✓
	5			997 8	5/29	7			996 7 ✓
3/23	6			997 5		8			998 4 ✓
3/28	7			997 6	6/1	9	41	0	997 0 ✓
	8			997 5	6/5	670			997 3 ✓
4/3	9	47	6	997 5		1			998 1 ✓
4/5	640			997 4	6/8	2			997 9 ✓
	1			998 1	6/14	3			998 0 ✓
4/6	2			997 8		4			997 1 ✓
4/11	3			997 2	6/15	5			997 1 ✓
	4			997 6		6			997 9 ✓
4/13	5			997 5					
	6			997 3					
4/20	7			997 7					
	8			997 9					
4/23	9	48	4	997 4					
4/25	650			997 8					
	1			998 3					
4/26	2			997 1					
5/3	3			997 4					
	4			998 3					
5/7	5			997 4					
5/9	6			997 5					
	7			997 3					
5/11	8			997 4					
5/14	9	44	7	899 6					

Fiscal 1957

ASSAYER'S REGISTER OF MINT FINE GOLD.

9-9331

DATE. 1956	NO. OF MELT.		FINENESS.	DATE.	NO. OF MELT.		FINENESS.
7/5	500		997 7	8/24	532		997 6 ✓
	1		998 4	8/29	3		997 8 ✓
	2		997 5		4		997 6 ✓
7/6	3		997 9	8/31	5		997 7 ✓
	4		998 3	9/10	6		997 9 ✓
	5		997 8		7		998 7 ✓
7/9	6		997 5	9/14	8		997 3 ✓
	7		997 9	9/13	9	54	997 1 ✓
	8		996 9		540	2	998 0 ✓
7/17	9	54	997 9		1		997 6 ✓
7/16	510		997 8	9/18	2		997 3 ✓
	1		997 0		3		998 2 ✓
	2		997 1	9/24	4		997 7 ✓
7/17	3		997 7	9/26	5		998 0 ✓
	4		998 0		6		997 8 ✓
7/19	5		997 6	9/28	7		996 8 ✓
7/27	6		997 2	10/2	8		997 0 ✓
	7		998 0		9	44	997 9 ✓
	8		997 9	10/4	550	9	997 6 ✓
8/1	9	53	998 0	10/9	1		997 4 ✓
	520		998 2		2		998 1 ✓
8/3	1		997 8	10/11	3		996 4 ✓
8/8	2		997 5	10/17	4		997 1 ✓
	3		997 8		5		997 7 ✓
8/10	4		997 8	10/19	6		997 9 ✓
8/15	5		997 7	10/24	7		997 8 ✓
	6		998 1		8		997 0 ✓
	7		997 7	10/26	9	48	996 9 ✓
	8		997 9	11/1	560	9	997 2 ✓
8/16	9	49	997 2		1		997 2 ✓
8/22	530	3	997 6	11/5	2		997 3 ✓
	1		998 2				

ASSAYER'S REGISTER OF MINT FINE GOLD.

9-2331

DATE.	No. OF MELT.		FINENESS.	DATE.	No. OF MELT.		FINENESS.
1956				1957			
"/7	563		997 5	"/16	595		997 0
	564		997 1		6		998 2
"/8	565		997 5	"/17	7		997 7
"/16	566		997 6	"/23	8		997 6
	567		997 9		9	48	998 1
"/19	568		996 5	"/24	600		997 9
	569	54	996 6	"/29	1		998 2
"/21	570		997 3		2		997 3
"/23	1		998 0	"/1	3		997 3
"/27	2		996 2	"/5	4		997 9
"/28	3		996 6		5		997 8
	4		997 9	"/8	6		997 7
12/3	5		997 6		7		997 8
12/6	6		997 4	"/13	8		997 9
	7		997 3		9	47	997 9
	8		997 0	"/15	610		997 4
12/12	9	50	995 8		1		997 5
	580		996 7	"/19	2		997 6
12/13	1		997 1	"/20	3		998 1
12/18	2		995 9	"/21	4		997 4
12/19	3		997 7	"/27	5		998 1
12/20	4		996 9	"/28	6		997 9
12/28	5		997 3		7		997 5
	6		997 2	"/7	8		997 4
	7		995 8		9	51	997 4
1957	8		997 2	"/8	620		997 9
"/2/57	9	49	997 0		1		997 3
	590		997 4	"/14	2		997 3
"/4			997 4	"/13	3		997 4
"/8	1		997 7		4		996 7
	2		997 0	"/15	5		997 4
"/14	3		998 0	"/20	6		997 6
	4						

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE. 1957	NO. OF MELT.		FINESS.	DATE. 1957	NO. OF MELT.		FINESS.
3/20	627		998 2	5/23	659	47 3	998 3
3/29	628		997 3		660		997 2
	629	44	997 7	5/29	661		996 6
	630		996 8		662		997 8
	631		996 3	5/31	663		997 3
4/4	632		997 1	6/5	664		997 4
	633		997 2		665		998 3
4/10	634		998 3	6/10	666		998 1
	635		997 3		667		997 3
	636		997 6	6/12	668		997 8
	637		997 9		669	47 4	998 3
4/12	638		996 3	6/13	670		997 4
	639	52	997 1	6/18	671		997 9
4/16/17	640		997 2		672		998 6
4/16	641		997 1				
4/19	642		997 9				
	643		899 8				
4/24	644		997 1				
	645		998 0				
4/25	646		997 0				
4/30	647		997 4				
	648		998 1				
5/3	649	46	996 9				
5/8	650		997 7				
	651		998 3				
5/9	652		997 2				
5/10	653		997 7				
	654		998 6				
	655		997 4				
	656		998 0				
5/16	657		996 0				
	658		997 3				

Fiscal 1958

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	No. OF MELT.		FINENESS.	DATE.	No. OF MELT.		FINENESS.
1957				1957			
7/1	501		9973	8/28	532		9969
	2		9970	8/29	533		9973
	3		9977	9/4	534		9976
7/2	4		9964		5		9978
	5		9978	9/5	6		9978
	6		9974	9/10	7		9978
7/5	7		9968		8		9975
7/9	8		9975	9/12	9		9979
	9		9976	9/17	540	53	8
7/11	510	49	9971		1		9978
	1		9969	9/19	2		9969
7/19	2		9981	9/26	3		9973
	3		9975		4		9979
	4		9973		5		9970
7/24	5		9974	10/1	6		9973
	6		9983	10/2	7		9979
7/26	7		9982	10/3	8		9965
7/30	8		9983		9		9959
	9		9985	10/8	550	56	7
8/6	520	50	9977		1		9977
	1		9976	10/10	2		9975
	2		9981	10/16	3		9981
8/8	3		9970		4		9966
8/13	4		9968		5		9969
	5		9973	10/18	6		9975
	6		9973	10/22	7		9981
8/15	7		9972		8		9971
8/21	8		9979	10/25	9		9964
	9		9980		560	75	8
8/23	530	35	9971		1		9981
8/28	1		9983	11/1	2		9981

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2331

DATE.	No. OF MELT.		FINESS.	DATE.	No. OF MELT.		FINESS.
1957				1957			
3/20	627		998 2	5/23	659	47 3	998 3
3/29	628		997 3		660		997 2
	629	44	997 7	5/29	661		996 6
	630		996 8		662		997 8
	631		996 3	5/31	663		997 3
4/4	632		997 1	6/5	664		997 4
	633		997 2		665		998 3
4/10	634		998 3	6/10	666		998 1
	635		997 3		667		997 3
	636		997 6	6/12	668		997 8
	637		997 9		669	47 4	998 3
4/12	638		996 3	4/13	670		997 4
	639	52	997 1	6/18	671		997 9
4/16/17	640		997 2		672		998 6
4/16	641		997 1				
4/19	642		997 9				
	643		899 8				
4/24	644		997 1				
	645		998 0				
4/25	646		997 0				
4/30	647		997 4				
	648		998 1				
5/3	649	46	996 9				
5/8	650		997 7				
	651		998 3				
5/9	652		997 2				
5/15	653		997 7				
	654		998 6				
	655		997 4				
	656		998 0				
5/16	657		996 0				
	658		997 3				

Fiscal 1958

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2201

DATE. 1957	No. OF MELT.		FINENESS.	DATE. 1957	No. OF MELT.		FINENESS.
7/1	501		9973	8/28	532		9969
	2		9970	8/29	533		9973
	3		9977	9/4	534		9976
7/2	4		9964		5		9978
	5		9978	9/5	6		9978
	6		9974	9/10	7		9978
7/5	7		9968		8		9975
7/9	8		9975	9/12	9		9979
	9		9976	9/17	540	53	9978
7/11	510	49	9971		1		9978
	1		9969	9/19	2		9969
7/19	2		9981	9/26	3		9973
	3		9975		4		9979
	4		9973		5		9970
7/24	5		9974	10/1	6		9973
	6		9983	10/2	7		9979
7/26	7		9982	10/3	8		9965
7/30	8		9983		9		9959
	9		9985	10/8	550	56	9977
8/6	520	50	9977		1		9977
	1		9976	10/10	2		9975
	2		9981	10/16	3		9981
8/8	3		9970		4		9966
8/13	4		9968		5		9969
	5		9973	10/18	6		9975
	6		9973	10/22	7		9981
8/15	7		9972		8		9971
8/21	8		9979	10/25	9		9964
	9		9980		560	75	9968
8/23	530	35	9971		1		9981
8/28	1		9983	11/1	2		9981

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE. 1957	NO. OF MELT.		FINENESS.	DATE. 1958	NO. OF MELT.		FINENESS.
"1/5	563		997 6	"1/15	594		996 8
"1/6	564		997 5		5		997 6
"1/8	5		998 0		6		997 4
	6		996 9	"1/23	7		997 6
"1/3	7		997 5		8		998 4
	8		997 2		9		996 3
	9		996 9		600	54 9	998 9
"1/15	570	73	997 1	"1/27	1		996 6
"1/20	1		997 2		2		996 8
	2		997 9		3		997 3
"1/25	3		996 3		4		997 4
"1/29	4		997 4	"1/31	5		997 5
	5		997 2		6		996 6
12/3	6		997 2		7		997 4
12/4	7		997 1	"2/5	8		997 6
	8		997 9		9		997 1
12/11	9		996 9	"2/10	610	60 8	997 8
12/18	580	49	997 5		1		996 7
	1		998 3	"2/18	2		996 9
12/12	2		998 0		3		997 6
	3		998 3	"2/19	4		996 6
12/26	4		997 2		5		996 4
	5		997 4		6		996 9
	6		998 1	"2/21	7		996 2
"1/6	7		997 2	"2/25	8		997 8
"1/9	8		997 2		9		997 0
	9		996 9	"2/27	620	75 9	996 9
"1/10	590	67	997 5	"3/5	1		996 5
1/11	1		997 6		2		997 6
"1/14	2		998 1	"3/7	3		996 4
"1/15	3		997 5	"3/12	4		997 0

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE	NO. OF MELT.		FINESS.	DATE	NO. OF MELT.		FINESS.
1958				1958			
3/12	625		998 0	5/15	656		996 6
3/13	626		996 9		657		997 3
3/20	627		997 3		658		996 2
	628		997 6		659		997 6
	629		997 3	5/16	660	48	996 5
3/27	630	82	996 9	5/21	661	5	996 7
3/31	631		997 7		662		996 9
	632		997 0	5/22	663		997 2
4/4	633		997 4	5/28	664		997 1
	634		997 8		665		997 1
4/10	635		996 3	6/4	666		995 7
	636		996 5		667		997 5
4/15	637		996 8		668		997 6
	638		998 1	6/10	669		997 1
	639		995 9		670	57	996 8
4/21	640	53	996 6	6/12	671		996 6
	641		998 6		672		997 4
	642		996 9	6/13	673		997 2
	643		997 7				
4/24	644		996 3				
	645		899 7				
4/28	646		998 0				
	647		997 3				
	648		996 0				
5/2	649		996 8				
	650	82	997 1				
	651		996 3				
5/8	652		997 2				
	653		997 7				
5/13	654		996 7				
	655		996 8				

Fiscal 1959 Deposited Melt Room

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2231

DATE. 1958	NO. OF MELT.		FINENESS.	DATE. 1958	NO. OF MELT.		FINENESS.	
6/25	500		997 2	8/29	531		997 2	
	1		998 0		2		998 2	124
	2		997 0		3		996 2	
	3		997 2	9/4	534		996 6	
	4		997 7		5		998 1	
6/27	5		997 5	9/8	6		997 1	
7/1	6		996 6		7		996 1	
	7		997 8	9/12	8		997 3	
7/7	8		996 8		9		997 0	
7/10	9		997 2		540	59	996 6	
	510	54	998 3		1		997 8	
7/14	1	3	997 2	9/17	2		998 0	
	2		997 2		3		998 0	
7/17	3		997 9	9/19	4		996 5	
	4		996 6	9/29	5		996 9	
7/18	5		996 7		6		997 6	
7/24	6		997 2	10/6	7		996 4	
	7		996 8		8		997 9	
7/25	8		996 8		9		997 3	
7/30	9		997 4	10/8	550	41	996 8	
	520	43	998 6	10/10	1		996 7	
8/1	1		997 5	10/9	2		997 1	
8/6	2		997 6	10/13	3		996 8	
	3		998 1	10/15	4		996 7	
8/8	4		997 4		5		997 2	
8/13	5		997 3	10/17	6		996 9	
	6		997 6	10/23	7		997 5	
8/15	7		995 4		8		997 2	
8/20	8		997 1		9		996 8	
	9		997 4	10/31	560	82	996 7	
8/21	530	46	996 5		1		997 8	

ASSAYER'S REGISTER OF MINT FINE GOLD.

9-2231

DATE.	NO. OF MELT.		FINENESS.	DATE.	NO. OF MELT.		FINENESS.
1958				1959			
10/31	562		9963	1/2	593		9964
11/7	563		9972	1/14	4		9970
	564		9976		5		9972
11/10	565		9963	1/16	6		9960
11/14	566		9976	1/21	7		9970
	567		9973		8		9971
11/18	568		9960	1/23	9		9966
	569		9961	1/29	600	49 70	9970
11/20	570	80 4	9974		1		9976
	1		9973	1/30	2		9966
11/24	2		9965	2/5	3		9970
12/1	3		9970		4		9977
	4		9971	2/6	5		9968
	5		9971	2/13	6		9963
	6		9972		7		9977
	7		9984		8		9959
	8		9965				
12/10	9		9966				
	580	76 1	9981				
12/12	1		9977				
12/19	2		9977				
	3		9970				
	4		9970				
12/29	5		9973				
	6		9974				
	7		9968				
1/5/59	8		9965				
	9		9980				
	590	64 3	9963				
1/7	1		9968				
	2		9964				

ASSAYER'S REGISTER OF MINT FINE GOLD.

1-2-11

DATE.

NO. OF
MELT.

FINESS.

DATE.

NO. OF
MELT.

FINESS.

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE 1958	NO. OF MELT.	FINESS.	DATE 1958	NO. OF MELT. 1958	FINESS.
10/27	1	999 6	11/3	11/32	999 6
	2	999 7		33	999 6
	3	999 6		4	999 4
	4	999 7	11/7	5	999 5
	5	999 6		6	999 6
10/28	6	999 6		7	999 6
	7	999 7		8	999 5
	8	999 7		9	999 7
	9	999 7		40 84	999 7
	10 49	999 5		1	999 6
	1	999 7		2	999 6
	2	999 5		3	999 6
	3	999 7		4	999 7
	4	999 8		5	999 4
	5	999 6		6	999 6
10/29	6	999 5	11/10	7	999 4
	7	999 7		8	999 5
	8	999 4		9	999 7
	9	999 7		50 90	999 6
	20 99	999 6		1	999 4
	1	999 5		2	999 6
11/3	2	999 3		3	998 0
	3	999 4		4	999 5
	4	999 7		5	999 2
	5	999 5	11/14	6	999 5
	6	999 6		7	999 6
	7	999 6		8	999 7
	8	999 7		9	999 5
	9	999 5		60 86	999 6
	30 73	999 5		1	999 6
	1	999 7		2	999 7

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2231

DATE. 1958	No. OF MELT.		FINENESS.	DATE.	No. OF MELT.		FINENESS.
"/14	63		999 6	11/20	94		999 3
	4		999 7		5		999 5
	5		999 7	11/24	6		999 4
	6		999 8		7		999 5
	7		999 8		8		999 5
"/18	8		999 9		9		999 2
	9		999 9		100	54 3	999 3
	70	44 8	999 8		1		999 0
	1		999 9		2		999 4
	2		999 9		3		999 1
	3		998 9		4		999 5
	4		999 5		5		999 4
	5		999 7		6		999 3
	6		999 7		7		999 4
	7		999 7		8		999 3
	8		999 7		9		999 3
"/20	9		999 6		110	41 2	999 2
	80	45 0	996 0		1		999 2
	1		999 6	11/25	2		999 1
	2		999 1		3		999 3
	3		999 6		4		999 1
	4		999 3		5		999 0
	5		999 5		6		999 3
	6		999 6		7		999 4
	7		999 4		8		999 3
	8		999 5		9		999 5
	9		999 7	11/26	120	47 4	999 4
	90	43 5	999 5		1		999 5
	1		999 5		2		999 4
	2		996 8		3		999 3
	3		999 4		4		998 9

ASSAYER'S REGISTER OF MINT FINE GOLD.

9-5231

DATE.	No. OF MELT.			FINENESS.	DATE.	No. OF MELT.			FINENESS.
1958									
11/26	125			999 5 ✓					
	6			999 0 ✓					
	7			999 4 ✓					
	8			999 3 ✓					
	9			998 9 ✓					
	130	48	3	999 3 ✓					
	1			999 0 ✓					
	2			998 8 ✓					
	3			999 4 ✓					
	4			999 1 ✓					
	5			999 3 ✓					
	6			999 6 ✓					
	7			999 5 ✓					
11/28	8			999 3 ✓					
	9			999 5 ✓					
	140	51	4	999 4 ✓					
	1			999 5 ✓					
	2			999 6 ✓					
	3			999 4 ✓					
	4			999 5 ✓					
	5			999 3 ✓					
	6			999 5 ✓					
	7			999 5 ✓					
	8			999 7 ✓					
12/1	9			999 5 ✓					
	150	58	6	999 6 ✓					
	1			999 6 ✓					
	2			999 6 ✓					
	3			999 5 ✓					
	4			999 7 ✓					
	5			999 6 ✓					
			CTA	999 6 ✓					

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2231

1958 DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
12/1	156	999 5	12/5	18 7	999 6
12/2	7	999 6	12/10	8	996 8
	8	999 6		9	998 8
	9	999 3		190 66	996 1
160 74	7	999 7		1	996 8
1	2	999 2		2	996 3
2	3	999 6		3	995 9
3	4	999 4		4	999 2
4	5	999 6		5	998 8
5	6	999 6		6	999 5
6	7	999 6		7	999 2
7	8	999 7		8	995 9
8	9	999 6	12/11	9	996 9
9	170 56	999 3		200 65	997 7
1	2	999 2		1	999 1
2	3	999 4		2	998 3
3	4	999 6		3	998 2
4	5	999 3		4	999 0
5	6	996 4		5	999 1
6	7	999 0		6	998 9
7	8	999 2		7	999 2
8	9	998 9		8	998 7
9	180 45	998 9		9	999 3
1	2	996 1		210 58	999 0
2	3	997 2		1	999 3
3	4	999 5	12/12	2	999 1
4	5	999 1		3	999 2
5	6	995 4		4	999 5
6	7	999 5		5	999 2
	8	999 5		6	999 6
	9	995 7		7	999 2
				8	999 3

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2221

DATE.	NO. OF MELT.			FINENESS.	DATE.	NO. OF MELT.			FINENESS.
1958									
12/12	219			999 5	12/18	250	57	3	999 3
12/15	220	51	6	999 6		1			999 3
	1			999 1		2			999 4
	2			999 4		3			999 5
	3			999 3		4			999 3
	4			999 4		5			999 3
	5			999 3		6			999 4
	6			999 4		7			999 4
	7			999 3		8			999 3
	8			999 5		9			999 7
	9			999 5		260	54	7	999 7
12/16	230	54	4	999 4		1			995 6
	1			999 5		2			999 6
	2			999 4	12/19	3			999 6
	3			999 6		4			999 6
	4			999 5		5			995 9
	5			999 5		6			995 5
	6			999 3		7			995 6
	7			999 3		8			999 1
	8			999 4		9	44	1	999 1
	9			999 4		270			999 5
	240	58	5	999 5		1			999 5
	1			999 2	12/29	2			999 8
12/17	2			999 3		3			999 7
	3			999 4		4			999 7
	4			999 2		5			996 8
	5			999 4		6			999 7
	6			999 5		7			999 3
	7			999 5		8			999 8
	8			999 6		9			999 5
12/18	9			999 4		280	45	6	999 6

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2231

DATE. 1958	NO. OF MELT.		FINENESS.	DATE. 1958	NO. OF MELT.		FINENESS.	
12/29	281	AIM	999 6	12/31	313		999 8	/
	2		999 7	1/5/59	4		999 6	/
	3		999 6		5		999 6	/
	4		999 7		6		999 7	/
	5		999 7		7		999 7	/
12/30	6		999 5		8		999 7	/
	7		999 6		9		999 8	/
	8		999 8	1/7	320	59 8	999 8	/
	9		999 5		1		999 6	/
290	58	5	999 5		2		999 8	/
	1		999 4		3		999 6	/
	2		999 6		4		999 6	/
	3		999 5		5		999 7	/
	4		999 7		6		999 8	/
	5		999 7		7		999 7	/
	6		999 7		8		999 8	/
	7		999 6		9		999 8	/
	8		999 5		330	57 8	999 8	/
12/31	9		999 7		1		999 8	/
	300	59	999 8	1/12	2	AIM	999 8	/
	1		999 7		3		999 8	/
	2		999 8		4		999 8	/
	3		999 7		5		999 7	/
	4		999 7		6		999 8	/
	5		999 7		7		999 7	/
	6		999 8		8		999 8	/
	7		999 8		9		999 7	/
	8		999 7		340	65 8	999 8	/
	9		999 7		1		999 7	/
310	56	7	999 7		2		999 8	/
	1		999 8		3		999 6	/
	2		999 7		4		999 6	/

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	NO. OF MELT.		FINENESS.	DATE.	NO. OF MELT.		FINENESS.	
1959								
1/12	345		999 7	1/16	377		999 7	
	6		999 8		8		999 6	
1/13	7		999 7		9		996 1	
	8		999 8		380	55 8	999 8	
	9		999 8		1		995 4	
350	52	7	999 7		2		996 2	
	1		999 8		3		999 5	
	2		999 7		4		999 4	
	3		999 7		5		999 7	
	4		999 8		6		999 7	
	5		999 7		7		999 7	
	6		999 8		8		999 7	
	7		999 8		9		999 5	
1/14	8		999 7		390	60 8	999 8	
	9		999 7	1/20	1		995 5	
360	56	8	999 8		2		999 8	
	1		999 7		3		999 6	
	2		999 7		4		999 7	
	3		999 8		5		999 8	
	4		999 8		6		999 8	
	5		999 8		7		999 7	
	6		999 7		8		999 7	
	7		999 7		9		999 7	
	8		999 8	1/21	400	49 8	999 8	
	9		999 7		1		999 6	
370	56	8	999 8		2		999 8	
	1		999 8		3		999 6	
1/16	2		999 8		4		999 8	
	3		999 8		5		999 8	
	4		999 8		6		999 8	
	5		999 4		7		995 6	
	6		999 7		8		999 8	

R2M

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2231

DATE.	NO. OF MELT.			FINESS.	DATE.	NO. OF MELT.			FINESS.
1959					1959				
1/21	409			998 6	1/26	441			999 8
	460	61	7	999 7		2			999 8
	411			999 7		3			999 7
	2			999 7		4			999 7
	3			999 7	1/27	5			998 1
	4			999 7		6			999 9
1/22	5			999 7		7			999 6
	6			999 6		8			999 8
	7			999 6		9			999 8
	8			999 7	450	58	3		999 3
	9			999 8		1			999 6
	420	59	6	999 6		2			999 9
	1			999 7		3			999 6
	2			999 7		4			999 8
	3			999 7		5			999 6
	4			999 7		6			999 9
	5			999 7	1/28	7			999 6
	6			999 8		8			999 9
	7			999 7		9			999 7
	8			999 7	460	54	8		999 8
	9			999 7		1			999 7
1/23	430	63	8	999 8		2			999 9
	1			999 6		3			999 8
	2			999 8		4			999 8
1/26	3			999 7		5			999 8
	4			999 9		6			999 9
	5			999 6		7			999 6
	6			999 8		8			999 7
	7			999 7	1/29	9			999 6
	8			999 9		470	52	7	999 7
	9			999 7		1			999 7
	440	49	6	999 6		2			999 7

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE 1959	No. OF MELT.		FINENESS.	DATE.	No. OF MELT.		FINENESS.
1/29	473		999 5	2/3	755		996 7
	4		999 7		6		999 8
	5		999 7		7		999 4
	6		999 2		8		999 8
	7		997 1 ^{adm}		9		999 6
1/30	8		999 8		760 55	7	999 7
	9		999 2		1		999 9
480	52	7	999 7		2		999 8
	1		999 5		3		999 8
	2		999 6	2/4	4		999 7
	3		999 6		5		999 8
	4		999 3		6		998 0
	5		999 4		7		999 9
	6		997 9		8		999 5
	7		999 6		9		997 1
	8		997 5		770 51	6	999 6
	9		997 7		1		999 6 ^{GT3}
490	59	7	997 7		2		999 5
	1		999 8		3		999 3
2/3	2		999 8	2/5	4		999 4
	3		999 9		5		999 4
	4		999 8		6		999 4
	5		999 5		7		999 5
	6		999 7		8		999 1
	7		999 7		9		999 6
	8		999 8		780 44	2	999 2
499			999 7		1		999 4
750	57	8	999 8		2		999 8
	1		999 7		3		999 6
	2		999 8		4		999 7
	3		999 7		5		999 7
	4		999 9		6		999 8

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	NO. OF MELT.		FINESS.	DATE.	NO. OF MELT.		FINESS.
1959				1959			
2/5	787		999 7	2/10	819		999 6
2/6	8		999 9		820	55 7	999 7
	9		999 7		1		999 8
	790	43 7	999 7		2		999 8
	1		999 8		3		999 7
	2		999 8		4		999 8
	3		999 6		5		999 7
2/9	4		999 8		6		999 8
	5		999 6		7		999 7
	6		999 7		8		999 9
	7		999 7		9		999 7
	8		999 7		830	43 8	999 8
	9		999 7		1		999 6
	800	59 7	999 7		2		999 9
	1		999 7		3		999 6
	2		999 8		4		999 7
	3		999 7		5		999 7
	4		999 8		6		999 6
	5		999 8		7		999 7
	6		999 9		8		999 6
	7		999 6		9		999 6
	8		999 8		840	42 8	999 8
	9		999 7		1		999 7
	810	54 9	999 9	2/11	2		999 8
	1		999 8		3		999 7
	2		999 9		4		999 8
	3		999 7		5		999 6
	4		999 9		6		999 8
2/10	5		999 7		7		999 8
	6		999 9		8		999 7
	7		999 7		9		999 7
	8		999 7		850	48 6	999 6

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2534

DATE.	NO. OF MELT.		FINENESS.	DATE.	NO. OF MELT.		FINENESS.
1959							
2/11	851		999 6	2/17	883		999 7
	2		999 8	2/19	4		999 6
	3		999 7		5		999 7
	4		999 9		6		999 8
	5		999 7		7		999 7
	6		999 8		8		999 7
2/16	7		999 6		9		999 7
	8		999 7	890	53	7	999 7
	9		999 6		1		999 8
860	50	7	999 7		2		999 6
	1		999 6		3		999 6
	2		999 7		4		999 6
	3		999 6		5		999 3
	4		999 9		6		999 8
	5		999 7		7		999 2
	6		999 9		8		999 4
	7		999 7		9		999 8
	8		999 7	900	57	6	999 6
2/17	9		999 6		1		999 5
	870	56	6	2/20	2		999 5
	1		999 7		3		999 5
	2		999 9		4		999 5
	3		999 7		5		999 6
	4		999 8		6		999 7
	5		999 7		7		999 7
	6		999 8		8		999 6
	7		999 7		9		999 6
	8		999 7	910	54	7	999 7
	9		999 7		1		999 8
880	56	7	999 7		2		999 5
	1		999 8		3		999 5
	2		999 8		4		999 5

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	No. OF MELT.	FINENESS.	DATE.	No. OF MELT.	FINENESS.
1/59			1/59		
2/20	915	999 6	2/26	947	999 7
	6	998 5		8	999 9
	7	998 4		9	999 6
	8	998 3	950 58 7		999 7
2/24	9	999 4		1	999 8
	920 55 5	998 5		2	999 8
	1	999 0		3	999 8
	2	999 9		4	999 8
	3	998 9		5	999 7
	4	999 9		6	999 9
	5	998 7		7	999 8
	6	999 9		8	999 8
	7	998 7	2/27	9	999 8
	8	999 9		96 0 63 7	999 7
	9	998 8		1	999 9
	930 54 8	999 8		2	999 7
	1	999 6		3	999 8
2/25	2	999 9		4	999 8
	3	999 7		5	999 8
	4	999 9		6	999 9
	5	999 7		7	999 7
	6	999 9	3/2	8	999 9
	7	999 6		9	999 7
	8	999 9		970 45 9	999 9
	9	999 7		1	999 9
	940 42 7	999 7		2	999 9
2/26	1	999 7		3	999 8
	2	999 8		4	999 9
	3	999 7		5	999 9
	4	999 9		6	999 9
	5	999 7		7	999 8
	6	999 9		8	999 9

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	No. OF MELT.			FINENESS.	DATE.	No. OF MELT.			FINENESS.
1959					1959				
3/2	979			999 8	3/5	1011			999 1
	980	54	8	999 8		2			999 9
	1			999 8		3			999 5
	2			999 7		4			999 8
	3			997 3		5			999 8
	4			998 0		6			999 8
	5			999 3		7			999 7
	6			999 7		8	45	3	992 3
	7			997 7		9			997 8
	8			999 7		1020			997 0
3/4	9			999 4		1			996 9
	990	45	5	999 5		2			996 9
	1			997 3		3			997 5
	2			999 8		4			997 1
	3			999 5	3/6	5			996 4
	4			999 7		6			999 0
	5			999 6		7			998 9
	6			999 6		8			999 8
	7			999 7		9			997 3
	8			999 7		1030	50	7	997 7
	9			999 4		1			998 1
	1000	41	7	999 9		2			998 3
	1			999 8		3			998 0
	2			999 8		4			999 4
	3			999 8		5			998 4
	4			999 8		6			998 4
	5			998 2		7			997 4
	6			999 7		8			997 7
	7			999 3		9			998 2
	8			999 9		1040	59	4	998 4
	9			999 6		1			998 3
3/5	1010	41	9	999 9		2			998 4

New
RefX 1018

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	NO. OF MELT.		FINENESS.	DATE.	NO. OF MELT.		FINENESS.
1959				1959			
3/6	1043		998 7	3/11	1075		999 6
	4		998 2		6		999 5
	5		998 7		7		999 8
	6		998 3		8		999 5
	7		998 3		9		999 6
	8		999 7		1080	49 7	999 7
3/9	9		998 5		1		999 6
	1050	64 5	998 5		2		999 4
	1		998 4		3		999 4
	2		997 8		4		999 8
	3		997 8	3/12	5		999 3
	4		998 1		6		999 9
	5		997 7		7		999 6
	6		998 3		8		999 8
	7		997 8		9		999 4
3/10	8		998 3		1090	70 9	999 9
	9		998 7		1		999 6
	1060	49 3	998 3		2		999 6
	1		998 4		3		999 6
	2		998 6		4		999 7
	3		998 0		5		999 7
	4		997 9		6		999 7
	5		998 2		7		999 8
	6		998 4		8		999 2
	7		998 5		9		998 8
	8		998 4	3/14	1100	63 7	998 7
	9		998 4		1		999 2
	1070	53 2	998 2		2		998 9
	1		998 1		3		999 1
	2		998 2		4		999 2
3/11	3		999 7		5		998 9
	4		999 6		6		998 9

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE. 1959	No. OF MELT.	FINENESS.	DATE. 1959	No. OF MELT.	FINENESS.
3/16	1107	998 9	3/19	1139	999 1
	8	998 9		1140 59 1	999 1
	9	998 9		1	999 0
	1110 49 0	999 0		2	999 0
	1	999 0		3	999 1
	2	999 0		4	998 9
	3	999 4	3/24	5	998 9
	4	999 2		6	998 4
3/17	5	999 0		7	998 7
	6	998 9	Alt	8	998 3
	7	999 2		9	998 4
	8	998 8		1150 62 3	998 3
	9	998 9		1	998 5
	1120 57 0	999 0		2	998 4
	1	999 1		3	998 3
	2	998 9		4	998 3
	3	998 9		5	998 4
3/18	4	999 4		6	998 0
	5	999 0	3/26	7	998 4
	6	999 1		8	997 9
	7	998 9		9	998 2
	8	999 1		1160 59 9	998 9
	9	999 0		1	998 2
3/19	1130 57 1	999 1		2	998 3
	1	999 1		3	998 2
	2	999 2		4	998 8
	3	999 0		5	998 9
	4	999 2		6	998 0
	5	999 2		7	998 0
	6	999 1		8	998 9
	7	999 0	3/27	9	998 6
	8	999 0		1170 43 2	998 2

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2391

DATE.	NO. OF MELT.		FINESS.	DATE.	NO. OF MELT.		FINESS.
1959							
3/27	1171		998 4	4/1	1203		998 2
	2		998 4		4		998 7
	3		998 6		5		998 8
	4		998 3		6		998 7
	5		998 1		7		999 6
	6		997 9	4/2	8		999 5
	7		998 2		9		999 8
	8		998 0		1210	54 7	999 7
	9		998 8		1		999 7
	1180	54 2	998 2		2		999 7
	1		998 2		3		999 8
	2		998 3		4		999 7
	3		998 9		5		999 7
3/31	4		998 3		6		999 8
	5		998 7		7		999 8
	6		998 5		8		999 8
	7		998 2		9		999 8
	8		998 9	4/7	1220	46 9	999 9
	9		998 7		1		999 8
	1190	43 9	997 9		2		999 8
	1		998 1		3		999 8
	2		998 3		4		999 8
	3		998 0		5		998 6
	4		998 8		6		999 7
	5		998 2		7		999 8
4/1	6		998 3		8		999 8
	7		998 0		9		999 8
	8		998 5		1230	55 7	999 7
	9		998 6		1		999 7
	1200	50 1	997 7	4/9	2		999 7
	1		998 3		3		999 5
	2		998 3		4		999 8

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE 1959	No. OF MELT.		FINESS.	DATE 1959	No. OF MELT.		FINESS.
4/9	1235		999 8	4/15	1267		999 9
	6		999 9		8		999 9
	7		999 9		9		999 9
	8		999 8		1270	61 9	999 9
	9		999 9	4/22	1		999 9
	1240	74 9	999 9		2		999 9
	1		999 9		3		999 8
	2		999 9		4		999 9
	3		999 9		5		999 8
4/10	4		999 8		6		999 9
	5		999 8		7		999 8
	6		999 8		8		999 8
	7		999 9		9		999 9
	8		999 8		1280	63 9	999 9
	9		999 9		1		999 7
	1250	61 9	999 9		2		999 9
	1		999 8	4/27	3		999 7
	2		999 8		4		999 9
	3		999 8		5		999 8
	4		999 8		6		999 9
	5		999 8		7		999 7
4/15	6		999 9		8		999 8
	7		999 9		9		999 8
	8		999 9		1290	65 7	999 7
	9		999 9		1		999 8
	1260	68 9	999 9		2		999 8
	1		999 8		3		999 9
	2		999 9		4		999 8
	3		999 9	4/28	5		999 8
	4		999 9		6		999 9
	5		999 9		7		999 9
	6		999 8		8		999 9

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	NO. OF MELT.		FINENESS.	DATE.	NO. OF MELT.	FINENESS.
1959						
4/28	1299		999 9			
	1300	64	9			
	1		999 9			
	2		999 9			
	3		999 9			
	4		999 9			
	5		999 9			
	6		999 9			
	7		999 8			
	8		999 9			
	9		999 8			
4/29	1310	58	9			
	1		999 5			
	2		999 4			
	3		997 4			
	4		997 5			
	5		998 0			
	6		997 4			
	7		997 3			
	8		997 0			
	9		997 0			
	1320	47	0			
			997 0			

Fiscal 1960

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	NO. OF MELT.	FINENESS.	DATE.	NO. OF MELT.	FINENESS.
1960			1960		
4/27	1	996 6	5/5	33	996 8
	2	997 0		34	997 3
	3	997 1		35	997 0
4/28	4	997 0		36	997 0
	5	997 1		37	997 1
	6	997 0		38	997 1
	7	997 0		39	997 1
	8	997 0	5/6	40	996 3
4/29	9	996 9		41	996 8
	10	997 3		42	997 1
	11	996 7		43	997 4
	12	997 1		44	996 8
	13	997 3		45	996 6
	14	997 3		46	996 6
	15	996 9		47	996 8
5/3	16	997 5		48	996 7
	17	996 5		49	997 4
	18	997 0	5/9	50	997 2
	19	996 4		51	996 6
	20	996 4		52	997 1
	21	996 7		53	997 2
5/5	22	997 0		54	997 3
	23	996 6		55	997 4
	24	996 7		56	996 9
	25	996 5		57	997 3
	26	997 1		58	997 2
	27	996 7		59	997 0
	28	996 8	5/12	60	997 5
	29	996 9		61	997 2
	30	996 8		62	997 1
	31	996 6		63	997 4
	32	996 7		64	996 9

Fiscal 1961

ASSAYER'S REGISTER OF MINT FINE GOLD.

9-2281

DATE	No. OF MELT.		FINENESS.	DATE.	No. OF MELT.		FINENESS.
1960				1960			
9/29	1		995 0	10/4	33		998 6
	2		995 8		4		999 7
	3		996 3	10/6	5		997 6
	4		996 0		6		997 0
	5		998 4		7		999 7
	6		999 3		8		999 4
	7		999 8		9		999 4
	8		999 8		40 46	7	999 7
	9		999 7		1		999 6
	10	56	996 1		2		999 8
9/30	11		999 1		3		999 8
	12		999 8		4		999 8
	13		999 8	10/10	5		999 8
	14		999 7		6		999 8
	15		999 9		7		999 3
	16		999 8		8		999 7
10/4	17		999 8		9		999 9
	18		999 8		50 40	8	999 8
	19		999 6		1		999 9
	20	45	999 8		2		999 8
	21		999 9		3		999 9
	22		999 9		4		999 6
	23		999 4	10/11	5		995 9
	24		999 8		6		996 3
	25		999 8		7		996 1
	26		999 9		8		999 2
	27		999 8		9		999 6
	28		999 9		60 39	0	999 0
	29		999 9		1		998 4
	30	46	999 9		2		996 3
	31		999 9		3		997 1
	32		999 8		4		996 7

ASSAYER'S REGISTER OF MINT FINE GOLD.

1-2001

DATE 1960	No. OF MELT.		FINENESS.	DATE 1960	No. OF MELT.		FINENESS.	
10/11	65		999 1	10/14	97		999 1	
	6		999 3		8		998 6	
	7		999 3		9		999 4	
	8		999 7		100	54	998 9	100
	9		999 9	10/17	1		999 4	
10/12	70	38	999 2		2		999 6	
	1		999 8		3		999 5	
	2		999 5		4		996 4	
	3		999 9		5		999 5	
	4		999 9		6		997 1	
	5		999 7		7		999 7	
	6		999 8		8		999 8	
	7		999 8		9		999 3	
	8		999 8		110	47	999 8	
	9		996 0		1		999 8	
	80	41	999 9		2		999 5	
10/13	1		999 4		3		999 5	
	2		999 8	10/18	4		999 8	
	3		999 8		5		999 3	
	4		999 9		6		999 5	
	5		999 8		7		999 8	
	6		998 7		8		999 9	
	7		999 6		9		999 8	
	8		999 6		120	40	999 9	
	9		999 8		1		999 9	
	90	40	999 9		2		999 9	
10/14	1		999 8		3		999 9	
	2		999 7		4		996 9	
	3		997 4		5		999 4	
	4		997 7		6		998 0	
	5		997 0		7		997 7	
	6		995 8		8		998 6	

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-5594

DATE. 1960	NO. OF MELT.			FINENESS.	DATE. 1960	NO. OF MELT.			FINENESS.
10/19	129			998 3	10/24	161			999 8
	130	48	4	999 4	10/25	2			999 8
	1			999 4		3			999 8
	2			998 9		4			999 8
	3			996 2		5			999 8
	4			997 6		6			999 9
	5			999 5		7			999 7
	6			999 4		8			999 9
	7			999 9		9			999 9
	8			999 7	170	53	6		999 6
	9			999 5	1				998 9
	140	56	8	999 8	10/26	2			999 7
10/20	1			999 2		3			999 4
	2			999 9		4			999 4
	3			999 8		5			999 7
	4			999 7		6			998 0
	5			999 8		7			998 8
	6			999 8		8			999 0
	7			999 9		9			998 4
	8			999 8	180	54	1		999 1
	9			999 6	1				999 7
	150	53	8	999 8	2				999 2
10/24	1			999 8	3				999 7
	2			999 9	4				999 9
	3			999 8	5				998 3
	4			999 8	6				998 4
	5			999 5	10/27	7			998 1
	6			999 0	8				999 5
	7			999 0	9				999 5
	8			998 8	190	47	7		999 7
	9			999 7	1				998 8
	160	61	1	999 1	2				999 6

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2231

DATE. 1960	NO. OF MELT.		FINESS.	DATE. 1960	NO. OF MELT.		FINESS.
10/27	193		998 7	11/1	225		998 2
	4		997 4		6		999 2
	5		997 7		7		999 0
	6		996 1		8		999 5
	7		997 2		9		999 7
	8		996 8		230	50 7	999 7
	9		996 4		1		999 9
	200 49	1	997 0		2		999 8
	1		998 2		3		999 9
	2		997 7		4		998 7
	3		998 2		5		999 9
10/28	4		998 0		6		999 4
	5		997 7		7		999 3
	6		997 8		8		999 8
	7		997 7		9		999 6
	8		998 0		240	55 Remelt	998 5
	9		997 1		1		999 4
	210 60	1	996 1	11/2	2		999 8
	1		998 0		3		999 5
	2		998 7		4		999 9
	3		998 2		5		999 9
	4		998 2		6		999 7
	5		997 9		7		999 8
	6		997 2		8		998 7
10/31	7		997 3		9		998 7
	8		999 8		250 51	5	998 5
	9		999 9		1		999 6
	220 68	9	999 9		2		998 6
	1		997 8		3		999 3
	2		998 6		4		998 3
	3		998 2		5		999 6
11/1	4		998 0		6		999 5

ASSAYER'S REGISTER OF MINT FINE GOLD.

0-2211

DATE.	NO. OF MELT.		FINESS.	DATE.	NO. OF MELT.		FINESS.
1960				1960			
11/3	257		999 8	11/8	289		999 1
	8		999 9		290	60 5	999 5
	9		999 8		1		998 7
	260	60 6	999 6		2		999 3
	1		999 9		3		999 7
	2		999 0		4		998 7
	3		999 8		5		999 7
	4		999 5		6		999 1
	5		999 8		7		999 8
	6		999 4		8		999 9
	7		998 9		9		999 8
	8		999 8		300	64 9	999 9
	9		999 8		1		999 8
	270	63 5	999 5		2		999 9
	1		999 3	12/1	3		999 9
11/4	2		998 9		4		999 9
	3		999 8		5		999 8
	4		999 9	11/9	6		999 2
	5		999 8		7		999 4
	6		999 8		8		999 3
	7		999 8		9		999 1
	8		999 7		310	63 6	999 6
11/8	9		999 2		1		999 0
	280	54 5	999 5		2		998 3
	1		999 9		3		999 9
	2		999 6		4		999 9
	3		999 8		5		999 9
	4		999 0		6		999 8
	5		999 9		7		999 5
	6		999 4		8		999 3
	7		999 8		9		999 4
	8		999 4		320	60 9	999 9

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2231

DATE.	NO. OF MELT.	FINENESS.	DATE.	NO. OF MELT.	FINENESS.
1960			1960		
"/9	321	999 8	"/14	353	999 9
	2	999 8		4	999 3
	3	997 6		5	999 9
	4	997 8		6	998 0
	5	998 8		7	999 8
	6	998 6		8	998 2
"/10	7	999 1		9	999 4
	8	998 9	360 39 3		998 3
	9	998 9		1	998 3
330 38 9		998 9		2	998 2
	1	999 3	"/15	3	998 9
	2	999 2		4	998 0
	3	998 5		5	999 5
	4	999 3		6	999 5
	5	999 1		7	999 8
	6	999 7		8	999 5
	7	999 3		9	999 9
	8	999 7	370 47 5		997 5
	9	999 8		1	997 7
340 34 6		999 6		2	997 1
	1	998 9		3	997 4
	2	999 9		4	997 0
"/14	3	999 9	"/16	5	997 1
	4	999 1		6	997 5
	5	999 8		7	997 5
	6	999 2		8	997 3
	7	999 9		9	998 4
	8	999 5	380 41 8		998 8
	9	999 9		1	999 4
350 38 4		998 4		2	999 7
	1	999 9		3	999 9
	2	999 4		4	999 8

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE. 1960	NO. OF MELT.		FINENESS.	DATE. 1960	NO. OF MELT.		FINENESS.
11/6	385		999 8	11/8	417		999 9
	6		999 8		8		999 8
	7		999 9		9		999 9
	8		999 9		420	59 9	999 9
	9		999 9		1		999 8
	390	14 9	999 9		2		999 9
	1		999 9		3		999 8
	2		999 9		4		999 9
11/7	3		999 9		5		999 8
	4		999 9		6		999 9
	5		999 6	11/21	7		999 9
	6		999 9		8		999 8
	7		999 2		9		999 3
	8		999 7		430	48 3	999 3
	9		999 9		1		999 9
	400	40 4	999 3		2		999 2
	1		999 9		3		999 6
	2		999 5	11/22	4		998 8
	3		999 8		5		999 6
	4		998 7		6		999 6
	5		999 8		7		999 8
	6		998 8		8		999 6
	7		999 8		9		999 9
	8		999 2		440	56 7	999 7
	9		999 7		1		999 8
	410	56 7	999 7		2		999 9
11/18	1		999 5		3		999 6
	2		999 0		4		999 2
	3		997 8		5		998 8
	4		997 7		6		998 6
	5		999 9		7		999 9
	6		999 8		8		999 6

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2251

DATE 1960	No. OF MELT.		FINENESS.	DATE 1960	No. OF MELT.		FINENESS.
"/22	449		999 9	"/24	481		999 8
	450	67 9	998 9		2		999 8
	1		999 6		3		999 7
	2		999 4		4		999 7
	3		999 6		5		999 7
	4		998 3		6		999 6
	5		997 5		7		999 7
	6		997 3		8		999 7
	7		997 6		9		999 7
	8		997 7		490	49 7	999 7
	9		997 2		1		999 7
"/23	460	63 2	998 2		2		999 7
	1		997 5		3		999 7
	2		997 4	"/28	4		999 7
	3		999 9		5		999 8
	4		999 6		6		999 7
	5		999 8		7		999 7
	6		999 8		8		999 9
	7		999 8		9		999 7
	8		999 9		500	60 8	999 8
	9		999 9		1		999 6
	470	52 3	999 3		2		999 7
	1		998 3		3		999 6
	2		998 8		4		999 8
	3		997 8		5		999 8
	4		997 5		6		999 7
"/24	5		999 7	"/29	7		999 5
	6		999 7		8		999 6
	7		999 7		9		999 6
	8		999 8		510	47 7	999 7
	9		999 7		1		999 7
	480	64 7	999 7		2		999 6

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	No. OF MELT.			FINENESS.	DATE.	No. OF MELT.			FINENESS.
1960					1960				
11/29	513			999 8 ✓	12/1	545			999 7 ✓
	4			999 6 ✓		6			999 9 ✓
	5			999 8 ✓		7			999 6 ✓
	6			999 7 ✓		8			999 7 ✓
	7			999 8 ✓		9			999 6 ✓
	8			999 5 ✓	530	70	7		999 7 ✓
	9			999 9 ✓		1			999 7 ✓
520	59	8		999 8 ✓		2			999 7 ✓
	1			999 7 ✓		3			999 7 ✓
	2			999 6 ✓		4			999 7 ✓
	3			999 7 ✓		5			999 4 ✓
	4			999 6 ✓		6			999 6 ✓
	5 ✓			999 6 ✓		7			999 1 ✓
11/30	6			999 6 ✓		8			999 6 ✓
	7			999 7 ✓		9			999 5 ✓
	8			999 6 ✓	560	62	8		999 8 ✓
	9			999 8 ✓	12/5	1			999 5 ✓
530	66	5		999 5 ✓		2			999 7 ✓
	1			999 9 ✓		3			999 6 ✓
	2			999 7 ✓		4			999 8 ✓
	3			999 9 ✓		5			999 8 ✓
	4			999 7 ✓		6			999 7 ✓
	5			999 7 ✓		7			999 8 ✓
	6			999 5 ✓		8			999 8 ✓
	7			999 9 ✓		9			999 7 ✓
	8			999 7 ✓	570	64	6		999 6 ✓
	9			999 9 ✓		1			999 8 ✓
540	58	6		999 6 ✓		2			999 8 ✓
	1			999 8 ✓		3			999 8 ✓
	2			999 6 ✓		4			999 6 ✓
	3			999 8 ✓		5			999 7 ✓
12/1	4			999 6 ✓		6			999 9 ✓

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2831

DATE.	NO. OF MELT.		FINESS.	DATE.	NO. OF MELT.		FINESS.
1960				1960			
12/5	577		999 7	12/6	609		999 5
	8		999 8	12/7	610	28 8	999 8
	9		999 7		1		999 6
580	58	9	999 9		2		999 8
	1		999 6		3		999 6
	2		999 8		4		999 9
	3		999 8		5		999 7
	4		999 7		6		999 6
	5		999 7		7		999 4
	6		999 7		8		999 7
	7		999 8		9		999 7
	8		999 8		620	43 5	999 5
	9		999 6		1		999 6
590	39	7	999 7		2		999 7
12/6	1		999 6		3		999 8
	2		999 8		4		999 8
	3		999 7	12/8	5		999 5
	4		999 7		6		999 8
	5		999 5		7		999 6
	6		999 7		8		999 7
	7		999 9		9		999 6
	8		999 8		630	40 8	999 8
	9		999 7		1		999 7
600	28	8	999 8		2		999 7
	1		999 7		3		999 6
	2		999 9		4		999 8
	3		999 6		5		999 6
	4		999 9		6		999 6
	5		999 6	12/12	7		999 7
	6		999 7		8		999 8
	7		999 6		9		999 7
	8		999 8		640	41 9	999 9

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE 1960	No. OF MELT.		FINENESS.	DATE. 1960	No. OF MELT.		FINENESS.
12/12	641		999 5	12/12	673		999 7
	2		999 8		4		999 9
	3		999 6		5		999 7
	4		999 8		6		999 8
	5		999 7		7		999 5
	6		999 6	12/13	8		999 8
	7		999 6		9		999 6
	8		999 6	680 34 8			999 8
	9		999 7		1		999 8
650 46 7			999 7		2		999 7
	1		999 8		3		999 7
	2		999 6		4		999 9
	3		999 6		5		999 7
	4		999 7		6		999 7
	5		999 6		7		999 7
	6		999 9		8		999 8
	7		999 5		9		999 7
	8		999 7	12/15	690 39 8		999 8
	9		999 7		1		999 7
660 36 8			999 7		2		999 7
	1		999 7		3		999 8
	2		999 7		4		999 7
	3		999 7		5		999 7
	4		999 6		6		999 9
	5		999 7		7		999 7
	6		999 5		8		999 8
	7		999 8		9		999 8
	8		999 7	700 42 8			999 8
	9		999 7		1		999 8
670 41 6			999 6		2		999 6
	1		999 6		3		999 7
	2		999 8		4		999 7

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE. 1960	No. OF MELT.		FINESS.	DATE. 1960	No. OF MELT.		FINESS.
12/15	705		999 6	12/19	737		999 6
	6		999 7		8		999 7
	7		999 7		9		999 7
	8		999 7		740	40 8	999 8
	9		999 6		1		999 6
	710	52 7	999 6	12/20	2		999 7
	1		999 7		3		999 7
	2		999 7		4		999 9
	3		999 6		5		999 6
	4		999 2		6		999 7
	5		999 6		7		999 7
	6		999 7		8		999 8
	7		999 3		9		999 6
	8		999 7		750	49 8	999 8
	9		999 7		1		999 6
	720	49 7	999 7		2		999 7
	1		999 6		3		999 7
	2		999 7		4		999 8
	3		999 8		5		999 3
	4		999 6		6		999 8
	5		999 6		7		999 4
	6		999 8		8		999 8
	7		999 7		9		999 4
	8		999 6		760	51 5	999 5
	9		999 8		1		999 4
	730	46 7	999 7		2		999 4
	1		999 5		3		999 4
12/16	2		999 5		4		999 4
	3		999 7		5		999 2
12/19	4		999 8		6		999 6
	5		999 7		7		999 8
	6		999 7		8		999 8

ASSAYER'S REGISTER OF MINT FINE GOLD.

3-5351

DATE.	No. OF MELT.		FINENESS.	DATE.	No. OF MELT.	FINENESS.
1960				1960		
12/20	769		999 7	801		997 6
12/21	770	48 6	999 6	12/28	2	999 8
	1		998 0		3	999 1
	2		998 3		4	999 7
	3		998 1		5	999 0
	4		998 6		6	998 8
	5		997 6		7	999 0
	6		998 4		8	999 0
	7		998 3		9	998 9
	8		997 8	810	38 9	998 9
	9		997 7		1	998 8
	780	50 5	997 5		2	999 0
12/22	1		997 9		3	998 7
	2		998 9		4	999 0
	3		998 9		5	999 0
	4		998 1		6	999 4
	5		998 6		7	999 4
	6		999 8		8	999 7
	7		997 8		9	999 3
	8		999 3	820	34 1	999 1
	9		998 8		1	999 1
	790	50 1	999 1		2	998 8
	1		999 3		3	999 3
	2		998 7	12/29	4	998 7
	3		998 8		5	999 2
	4		998 3		6	998 7
	5		998 9		7	998 8
	6		998 0		8	998 3
	7		999 1		9	998 0
	8		998 2	830	34 6	998 6
	9		998 0		1	999 0
	800	52 7	998 6		2	997 6

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE 1960	No. of Melt.		FINESS.	DATE 1960	No. of Melt.		FINESS.
12/29	833		997 9	1/30	865		999
	4		999 8		6		999 8
	5		999 1		7		996 3
	6		999 9	1/31	8		999 7
	7		997 9	1/31	9		997 4
	8		999 9		870	34	999 7
	9		999 6		1		997 6
840	31	7	999 7		2		999 8
	1		999 1		3		999 4
	2		998 7		4		999 6
	3		999 5		5		997 9
	4		999 6		6		998 2
	5		999 6		7		997 8
	6		999 7		8		998 5
	7		999 7		9		999 3
	8		998 8		880	33	998 2
	9		999 7		1		998 0
12/30	850	40	999 9		2		999 8
	1		999 7		3		999 8
	2		999 8		4		999 8
	3		999 8		5		999 8
	4		999 9		6		999 9
	5		998 4		7		999 9
	6		999 5		8		999 8
	7		999 9		9		998 8
	8		999 8		890	36	999 8
	9		999 5		1		999 7
860	30	8	999 8		2		999 5
	1		999 2		3		999 5
	2		999 9		4		999 8
	3		998 9		5		999 7
	4		999 7		6		999 7

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2554

DATE.	No. OF MELT.		FINENESS.	DATE.	No. OF MELT.		FINENESS.
1961				1961			
1/6	897		999 5	1/11	929		999 6
	8		999 8		930	37	998 9
	9		999 7		1		999 7
	900	39	997 6		2		998 5
	1		999 9		3		999 8
	2		997 8		4		998 7
	3		999 9		5		998 6
	4		999 4		6		998 3
	5		999 7		7		998 5
	6		999 0		8		998 3
	7		999 0		9		998 9
	8		998 9		940	38	999 5
	9		999 0		1		998 6
	910	43	999 5		2		999 1
	1		999 6		3		998 3
	2		999 9		4		998 2
	3		999 7		5		999 8
	4		999 3		6		997 1
	5		999 3		7		999 8
	6		998 3		8		999 4
	7		998 7		9		999 8
1/9	8		998 5		950	33	998 7
	9		998 9		1		999 8
	920	40	998 8		2		998 7
	1		998 7		3		999 7
	2		998 5		4		998 8
	3		997 8		5		999 9
	4		998 0	1/12	6		998 8
	5		998 2		7		999 9
	6		998 2		8		999 6
	7		998 5		9		999 9
	8		998 3		960	35	999 6

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE. 1961	No. OF MELT.		FINENESS.	DATE. 1961	No. OF MELT.		FINENESS.
1/12	961		999 8	1/13	993		996 2 ✓
	2		999 7		4		996 1 ✓
	3		999 8		5		995 6 ✓
	4		999 7		6		996 1 ✓
	5		999 9		7		996 4 ✓
	6		999 2	1/16	8		996 4 ✓
	7		999 9		9		997 2 ✓
	8		998 6		1000	45 4	997 3 ✓
	9		999 9		1		997 7 ✓
	970	39 4	998 4		2		997 2 ✓
	1		999 9		3		998 1 ✓
1/10	2		998 2		4		998 1 ✓
	3		999 9		5		997 7 ✓
	4		998 4		6		997 4 ✓
	5		999 8		7		998 6 ✓
	6		999 4		8		998 3 ✓
	7		999 8		9		998 7 ✓
	8		999 8		1010	35 1	998 1 ✓
	9		999 2		1		998 4 ✓
	980	44 9	998 9		2		998 2 ✓
	1		999 1		3		998 3 ✓
	2		998 8		4		998 0 ✓
	3		998 3		5		998 1 ✓
	4		997 5		6		998 1 ✓
	5		997 4		7		998 1 ✓
	6		997 5		8		998 4 ✓
	7		997 5		9		998 5 ✓
	8		997 3		1020	41 6	998 6 ✓
	9		997 7		1		998 5 ✓
	990	39 1	997 1	10/18	2		998 8 ✓
	1		997 0		3		998 8 ✓
	2		997 1		4		998 4 ✓

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2571

DATE.	No. OF MELT.		FINENESS.	DATE.	No. OF MELT.		FINENESS.
1961				1961			
1/18	1025		998 4	1/19	1057		999 2
	6		998 3		8		999 2
	7		998 4		9		999 0
	8		998 3		1060 30	0	999 0
	9		998 3		1		999 0
	1030 42	4	998 4		2		998 8
	1		998 3		3		998 8
	2		998 2		4		998 8
	3		998 3		5		999 1
	4		998 7	1/20	6		999 2
	5		999 0		7		998 7
	6		999 1		8		999 3
	7		998 9		9		999 1
	8		999 1		1070 34	0	999 0
	9		999 1		1		998 6
	1040 33	9	998 9		2		998 9
	1		999 0		3		998 7
	2		999 0		4		999 1
	3		999 0		5		998 8
	4		999 1		6		999 0
1/19	5		999 0		7		998 4
	6		998 9		8		999 2
	7		999 4		9		999 0
	8		999 3		1080 34	8	998 8
	9		999 3		1		998 6
	1050 36	3	999 3		2		998 6
	1		999 1		3		998 6
	2		999 2		4		998 5
	3		999 1		5		998 4
	4		999 1		6		998 7
	5		999 3		7		998 4
	6		999 3		8		998 9

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	No. OF		FINENESS.	DATE.	No. OF		FINENESS.
1961	MELT.			1961	MELT.		
1/20	1089		997 8	1/25	1121		997 9
	1090	27	997 7		2		997 7
	1		998 0		3		997 5
	2		997 7		4		997 7
	3		997 8		5		998 2
	4		997 8		6		997 9
1/24	5		997 9		7		997 9
	6		997 7		8		998 0
	7		998 3		9		997 9
	8		998 2		1130	32	998 6
	9		998 1		1		997 7
	1100	26	998 0		2		997 9
	1		998 1		3		998 2
	2		998 0		4		998 3
	3		998 4		5		998 3
	4		998 5		6		998 1
	5		997 6		7		997 7
	6		997 3		8		997 8
	7		997 5	1/26	9		997 8
	8		997 8		1140	37	997 7
	9		998 0		1		997 5
	1110	37	997 8		2		997 3
	1		997 7		3		997 4
	2		998 0		4		997 6
	3		997 4		5		998 9
	4		997 7		6		997 5
	5		997 8		7		998 2
	6		997 4		8		997 5
	7		997 8		9		997 9
	8		998 0		1150	34	997 6
	9		997 5		1		997 8
1/25	1120	36	997 7		2		997 8

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	NO. OF MELT.	FINENESS.	DATE.	NO. OF MELT.	FINENESS.
1961			1961		
1/26	1153	997 6	1/30	1185	997 2
	4	997 8		6	997 5
	5	997 5		7	997 7
	6	997 4		8	998 0
	7	997 2		9	997 7
	8	997 7		1190	997 3
	9	997 5		1	997 4
	1160	997 8		2	997 7
	1	997 5		3	997 5
	2	997 9		4	997 8
	3	997 5		5	997 8
	4	997 5		6	997 9
	5	997 5		7	998 4
	6	997 7		8	999 2
	7	997 8		9	997 9
	8	997 6		1200	997 8
	9	997 7		1	999 5
	1170	997 6		2	999 5
	1	997 7		3	999 6
	2	997 7		4	998 5
	3	997 9		5	999 1
	4	998 3		6	999 1
	5	998 2		7	999 1
	6	997 8		8	999 4
	7	997 6		9	999 1
	8	997 7		1210	999 3
	9	997 8		1	999 1
	1180	997 4		2	999 2
	1	997 7		3	999 1
	2	997 4		4	999 1
	3	997 5		5	999 8
	4	997 6		6	999 5

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE. 1961	No. OF MELT.		FINENESS.	DATE. 1961	No. OF MELT.		FINENESS.
2/1	1217		999 4	2/6	1249		999 6
	8		999 2		1250	50	999 6
	9		998 8		1	7	999 7
	1220	30	998 7		2		999 8
2/2	1		999 4		3		999 6
	2		999 6		4		999 8
	3		998 8		5		999 6
	4		999 7		6		999 8
	5		998 9		7		999 6
	6		998 9		8		999 8
	7		999 4		9		999 7
	8		999 4		1260	35	999 5
	9		999 7		1	5	999 5
	1230	34	999 6		2		999 4
	1		999 6		3	✓	999 7
	2		999 6	2/7	4		999 7
	3		999 4		5		999 6
	4		999 7		6		999 9
	5		999 2		7		999 7
	6		999 8		8		999 8
	7		999 4		9		999 9
	8		999 3		1270	45	999 7
	9		999 6		1	7	999 5
	1240	30	999 7	2/8	2		999 4
	1		999 8		3		999 6
	2		999 9		4		999 6
	3		999 5		5		999 5
2/6	4		999 3		6		999 6
	5		999 8		7		999 5
	6		999 6		8		999 5
	7		999 7		9		999 6
	8		999 7		1280	45	999 6

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2237

DATE.	NO. OF MELT.		FINENESS.	DATE.	NO. OF MELT.	FINENESS.	
1961				1961			
2/8	1281		999 6	2/3	1313	999 7	
	2		999 6		4	999 6	
	3		999 8		5	999 7	
	4		999 8		6	999 7	
	5		999 6		7	999 6	
	6		999 5		8	999 6	
	7		999 4		9	998 8	
	8		999 7		1320	999 6	
	9		999 5		1	998 9	
	1290	41	999 6		2	998 8	
2/9	1		999 7		3	999 6	
	2		999 7		4	999 7	
	3		999 8		5	999 9	
	4		999 8		6	999 8	
	5		999 5		7	999 7	
	6		999 6		8	999 6	
	7		999 6		9	999 7	
	8		999 6		1330	999 8	
	9		999 6	2/14	1	999 6	
	1300	43	999 7		2	999 8	
	1		999 7		3	999 6	
	2		999 5		4	999 7	
	3		999 6		5	999 6	
	4		999 6		6	999 7	
	5		999 7		7	999 7	
	6		999 6		8	999 5	
	7		999 7		9	999 7	
	8		999 7		1340	999 7	
	9		999 7		1	999 6	
	1310	47	999 9		2	999 6	
	1		999 6		3	999 7	
2/13	2		999 7		4	999 7	

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2251

DATE. 1961	No. OF MELT.	FINENESS.	DATE. 1961	No. OF MELT.	FINENESS.
2/14	1345	999 6	2/16	1377	999 7
	6	999 7		8	999 8
	7	999 7		9	999 6
	8	999 6	1380	44	999 6
	9	999 6		1	999 7
1350	53	999 7		2	999 7
	1	999 6		3	999 8
	2	999 7		4	999 6
	3	999 6		5	999 8
	4	999 8		6	999 7
	5	999 7		7	999 9
	6	999 7		8	999 6
	7	999 8		9	999 6
	8	999 7	1390	42	999 6
	9	999 8		1	999 5
2/16	1360	999 6		2	999 6
	1	999 7	2/20	3	999 8
	2	999 6		4	999 6
	3	999 9		5	999 8
	4	999 8		6	999 5
	5	999 8		7	999 6
	6	999 8		8	999 6
	7	999 9		9	999 4
	8	999 9	1400	36	999 7
	9	999 6		1	999 8
1370	46	999 6		2	999 7
	1	999 6		3	999 8
	2	999 8		4	999 6
	3	999 8		5	999 8
	4	999 8		6	999 5
	5	999 7		7	999 9
	6	999 7		8	999 8

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE. 1961	NO. OF MELT.			FINENESS.	DATE. 1961	NO. OF MELT.			FINENESS.	
2/20	1409			999 6	2/23	1441			999 8	F.K. 1965 also see 9/23/65
	1410	40	5	999 5		2			999 9	102159
	1			999 6		3			999 1	
	2			999 7		4			999 8	
	3			999 6	2/27	5			999 7	
	4			999 7		6			999 0	
	5			999 7		7			999 6	
	6			999 7		8			999 5	
	7			999 7		9			999 7	
	8			999 6		1450	4	7	999 7	
	9			999 6		1			999 0	
2/21	1420	36	7	999 7		2			999 3	
	1			999 6		3			999 1	
	2			999 8		4			999 1	
	3			999 5		5			999 2	
	4			999 9		6			999 6	
	5			999 8		7			999 4	
	6			999 7		8			999 3	
	7			999 6	3/1	9			999 4	
	8			999 8		1460	40	4	999 4	
	9			999 7		1			999 4	
	1430	36	7	999 7		2			999 3	
	1			999 8		3			999 3	
	2			999 7		4			999 5	
	3			999 8		5			999 3	
	4			999 9		6			997 0	
	5			999 7		7			997 3	
2/23	6			999 7		8			997 3	
	7			999 8		9			996 9	
	8			999 7		1470	37	8	996 8	
	9			999 7		1			996 8	
	1440	36	7	999 7		2			997 0	

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2231

DATE 1961	No. OF MELT.	FINENESS.	DATE 1961	No. OF MELT.	FINENESS.
3/1	1473 ✓	997 3	3/6	1505	996 1 ✓
3/2	4	997 1 ✓		6	997 2 ✓
	5	997 1 ✓		7	997 1 ✓
	6	997 1 ✓		8	997 3 ✓
	7	996 7 ✓		9	996 7 ✓
	8	997 1 ✓	1510 38	7	997 7 ✓
	9	997 2 ✓			
	1480 40 3	997 3 ✓			
	1	997 4 ✓			
	2	997 1 ✓			
	3	997 5 ✓			
	4	997 1 ✓			
3/3	5	996 9 ✓			
	6	997 1 ✓			
	7	997 1 ✓			
	8	997 2 ✓			
	9	997 4 ✓			
	1490 47 8	996 8 ✓			
	1	997 2 ✓			
	2	997 4 ✓			
	3	997 2 ✓			
	4	997 1 ✓			
3/6	5	996 4 ✓			
	6	997 2 ✓			
	7	996 8 ✓			
	8	997 2 ✓			
	9	996 8 ✓			
	1500 51 9	996 9 ✓			
	1	997 1 ✓			
	2	996 8 ✓			
	3	997 3 ✓			
	4	997 0 ✓			

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1962					
5/16	1	997 2	5/17	33	997 2 ✓
	2	996 8		34	997 4 ✓
	3	996 9		35	997 0 ✓
	4	996 8		36	997 0 ✓
	5	997 2		37	997 2 ✓
	6	997 3		38	997 3 ✓
	7	996 9		39	997 1 ✓
	8	997 5		40	997 2 ✓
	9	997 3		41	997 2 ✓
	10	997 6		42	997 4 ✓
	11	997 1		43	997 1 ✓
	12	997 0		44	997 0 ✓
	13	997 1		45	997 0 ✓
	14	997 4	5/25	46	997 3 ✓
	15	996 8		47	997 4 ✓
	16	996 5		48	997 1 ✓
	17	997 1		49	997 2 ✓
5/8	18	996 8		50	996 8 ✓
	19	997 1		51	997 2 ✓
	20	997 2		52	996 9 ✓
	21	996 8		53	996 9 ✓
	22	997 0		54	997 3 ✓
	23	997 0		55	997 6 ✓
	24	997 5		56	997 3 ✓
	25	996 9		57	996 7 ✓
	26	997 1		58	996 8 ✓
	27	996 9		59	997 4 ✓
	28	997 0		60	997 7 ✓
	29	997 3		61	997 1 ✓
	30	996 9		62	996 9 ✓
5/22	31	997 2		63	997 0 ✓
	32	996 9		64	997 0 ✓

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2231

DATE.	NO. OF MELT.	FINESS.	DATE.	NO. OF MELT.	FINESS.
5/22	65	996 9 ✓			
	66	996 8 ✓			
	67	996 7 ✓			
	68	997 4 ✓			
	69	997 0 ✓			
	70	997 2 ✓			
	71	997 0 ✓			
	72	996 9 ✓			
	73	997 0 ✓			
	74	997 5 ✓			
	75	997 3 ✓			
	76	997 0 ✓			

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE	No. OF MELT.	FINESS.	DATE	No. OF MELT.	FINESS.
1963 6/3	1	997 3	6/11	33	997 2
	2	997 3		34	996 6
	3	997 6		35	996 6
	4	997 3		36	997 3
	5	997 4		37	997 2
	6	997 9		38	997 5
	7	997 1		39	997 1
	8	997 8		40	996 9
	9	998 0		41	997 2
	10	997 7		42	997 0
6/7	11	997 7	6/12	43	997 1
	12	998 3		44	997 0
	13	997 0		45	997 0
	14	996 8		46	997 0
	15	997 8		47	996 9
	16	997 7		48	996 9
	17	997 1		49	996 8
	18	997 6		50	997 0
	19	997 0		51	997 4
	20	997 1		52	997 6
6/11	21	996 8	6/13	53	997 4
	22	997 1		54	997 5
	23	996 8		55	997 7
	24	996 8		56	997 2
	25	996 8		57	997 0
	26	997 0		58	996 8
	27	997 6		59	997 0
	28	997 4		60	996 7
	29	997 0			
	30	996 9			
	31	997 1			
	32	996 3			

Fiscal

2-2231

ASSAYER'S REGISTER OF MINT FINE GOLD.

1964

DATE	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
	1	997 4 ✓	-	33	997 6 ✓
	2	996 8 ✓		34	997 4 ✓
	3	997 3 ✓		35	997 4 ✓
	4	997 1 ✓		36	997 3 ✓
	5	996 9 ✓		37	997 4 ✓
	6	996 6 ✓		38	997 2 ✓
	7	997 2 ✓		39	997 6 ✓
	8	997 3 ✓		40	997 7 ✓
	9	997 0 ✓		41	998 0 ✓
	10	997 5 ✓		42	997 8 ✓
	11	997 7 ✓		43	998 0 ✓
	12	998 1 ✓		44	997 8 ✓
	13	997 7 ✓		45	997 7 ✓
	14	997 6 ✓		46	997 7 ✓
	15	997 5 ✓		47	997 7 ✓
	16	997 6 ✓		48	997 2 ✓
	17	997 7 ✓		49	997 9 ✓
	18	998 0 ✓		50	998 0 ✓
	19	997 4 ✓		51	997 8 ✓
	20	997 8 ✓		52	997 7 ✓
	21	997 7 ✓		53	998 0 ✓
	22	997 4 ✓		54	997 8 ✓
	23	997 3 ✓		55	998 0 ✓
	24	997 2 ✓		56	997 6 ✓
	25	998 1 ✓		57	997 8 ✓
	26	997 8 ✓		58	997 5 ✓
	27	997 8 ✓		59	997 6 ✓
	28	997 8 ✓		60	997 6 ✓
	29	997 6 ✓		61	997 6 ✓
	30	997 5 ✓		62	997 3 ✓
	31	997 4 ✓			
	32	997 5 ✓			

mtr
627

ASSAYER'S REGISTER OF MINT FINE GOLD.

Final

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1965					
November	1	9975 ✓		33	9976 ✓
	2	9979 ✓		34	9977 ✓
	3	9980 ✓		35	9975 ✓
	4	9978 ✓		36	9973 ✓
	5	9974 ✓		37	9974 ✓
	6	9976 ✓		38	9978 ✓
	7	9977 ✓		39	9975 ✓
	8	9973 ✓		40	9976 ✓ <i>OK</i>
	9	9975 ✓		41	9975 ✓
	10	9976 ✓ <i>OK</i>		42	9977 ✓
	11	9976 ✓		43	9972 ✓
	12	9978 ✓		44	9973 ✓
	13	9973 ✓		45	9972 ✓
	14	9976 ✓		46	9975 ✓
	15	9975 ✓		47	9973 ✓
	16	9978 ✓		48	9969 ✓
	17	9979 ✓		49	9972 ✓
	18	9977 ✓		50	9972 ✓ <i>OK</i>
	19	9979 ✓		51	9974 ✓
	20	9978 ✓ <i>OK</i>		52	9974 ✓
	21	9971 ✓		53	9974 ✓
	22	9969 ✓		54	9976 ✓
	23	9968 ✓		55	9971 ✓
	24	9977 ✓		56	9974 ✓
	25	9973 ✓		57	9977 ✓
	26	9977 ✓		58	9972 ✓
	27	9975 ✓		59	9974 ✓
	28	9974 ✓		60	9975 ✓ <i>9976 Burn</i>
	29	9977 ✓			9974 ✓
	30	9978 ✓ <i>OK</i>			5305 ✓ <i>to 1965</i>
	31	9974 ✓			
	32	9973 ✓			

May

MSX-60
#1 Rec. R-1
#2 Rec. MR-2

Fiscal

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2231

DATE	No. OF MELT.		FINESS.	Bar FG	No. OF MELT.	FINESS.
1966			6019			
Sept 23/65	1	Bar	✓ 9998	}	Made for Cr D: See melt 1442.	
	2	✓	✓ 9998		50	Burs = lat #323 2/23/1961
	3	✓	✓ 9998		50	" = 324
	1	Recovery	✓ 8488	83.2	9	" = 328

1966

ASSAYER'S REGISTER OF MINT FINE GOLD.

Fiscal 1966

DATE.	NO. OF MELT.	FINESS.	DATE.	NO. OF MELT.	FINESS.
		Gold			
May 27/66	1	997 1 ✓		33	997 3 ✓
	2	997 2 ✓		34	997 8 ✓
	3	996 5 ✓		35	997 3 ✓
	4	997 8 ✓		36	997 5 ✓
	5	997 8 ✓		37	997 2 ✓
	6	997 7 ✓		38	76 ✓
	7	997 5 ✓		39	75 ✓
	8	997 4 ✓		40	78 ✓
	9	997 7 ✓		41	77 ✓
	10	997 5 ✓		42	72 ✓
	11	997 6 ✓		43	74 ✓
	12	997 4 ✓		44	71 ✓
	13	997 2 ✓		45	75 ✓
	14	997 5 ✓		46	74 ✓
	15	997 4 ✓		47	76 ✓
	16	997 0 ✓		48	74 ✓
	17	997 1 ✓		49	70 ✓
	18	997 0 ✓		50	74 ✓
	19	997 3 ✓		1	70 ✓
	20	997 3 ✓		2	72 ✓
	21	997 0 ✓		3	996 9 ✓
	22	997 6 ✓		4	997 5 ✓
	23	997 3 ✓		5	79 ✓
	24	997 4 ✓		6	77 ✓
	25	997 5 ✓		7	78 ✓
	26	997 3 ✓		8	78 ✓
	27	997 4 ✓		9	73 ✓
	28	997 5 ✓		60	75 ✓
	29	997 3 ✓		1	70 ✓
	30	997 5 ✓		2	73 ✓
	31	997 5 ✓		3	72 ✓
	32	997 4 ✓		4	72 ✓

X-64 "Kilo" from last melt #64 - 997.2
No sample submitted to lab.

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2251

H	DATE.	NO. OF MELT.	FINENESS.	DATE.	NO. OF MELT.	FINENESS.
		33	9973			
		4	9978			
		5	9973			
		6	9975			
		7				
		8				
		9				
		40				
		1				
		2				
		3				
		4				
		5				
		6				
		7				
		8				
		9				
		50				
		1				
		2				
		3				
		4				
		5				
		6				
		7				
		8				
		9				
		60				

see other side

J. 9. 1967

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
<i>3/2/67</i>					
	1	9972 ✓		33	9976 ✓
	2	67 ✓		34	73 ✓
	3	70 ✓		35	74 ✓
	4	69 ✓		36	76 ✓
	5	70 ✓		37	76 ✓
	6	66 ✓		38	77 ✓
	7	70 ✓		39	75 ✓
	8	70 ✓		40	76 ✓
	9	74 ✓		41	72 ✓
	10	78 ✓		42	78 ✓
	11	76 ✓		43	77 ✓
	12	79 ✓		44	75 ✓
	13	70 ✓		45	78 ✓
	14	73 ✓		46	76 ✓
	15	72 ✓		47	75 ✓
	16	75 ✓		48	78 ✓
	17	72 ✓		49	75 ✓
	18	75 ✓		50	80 ✓
	19	73 ✓		51	79 ✓
	20	75 ✓		52	76 ✓
	21	76 ✓		53	76 ✓
	22	73 ✓		54	75 ✓
	23	72 ✓		55	70 ✓
	24	73 ✓		56	73 ✓
	25	75 ✓		57	73 ✓
	26	76 ✓		58	9968 ✓
	27	75 ✓		59	9971 ✓
	28	72 ✓		60	73 ✓
	29	74 ✓		61	76 ✓
	30	80 ✓		62	74 ✓
	31	80 ✓			
	32	77 ✓			

very good

Barium 997.6

Barium 997.8

Barium 997.0

Barium 997.5

5/23 996.64

Barium 997.3

Barium 997.0

997.3

Box 62 420000

Tiscal 1968

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1968					
2/9	1	997 4	2/16	33	997 7
	2	997 3		4	997 6
	3	997 3		35	997 7
	4	997 0		6	997 7
	5	997 5		7	997 1
	6	997 5		8	997 8
	7	997 4		9	997 6
	8	997 8		40	997 5
	9	997 5		1	997 5
	10	997 4		2	997 3
	1	997 7		3	997 3
	2	997 5		4	996 9
	3	997 2		45	997 5
	4	997 3		6	997 4
	15	997 4		7	997 2
	6	997 5		8	997 2
	7	997 3		9	998 0
	8	997 2		50	997 6
	9	997 3		1	997 3
	20	997 8		2	997 4
	1	998 1		3	997 7
	2	997 9		4	997 9
	3	997 8		55	997 7
	4	997 9		6	997 6
	25	998 1		7	997 9
	6	997 4		8	997 9
	7	997 3		9	997 8
	8	997 6		60	997 6
	9	997 6		1	997 9
	30	997 4		2	997 6
	1	997 5			
	2	997 7			

ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE.	NO. OF MELT.	FINESS.	DATE.	NO. OF MELT.	FINESS.
1969 7/24	#54 of 120 1468	997.9			
None in Fiscal 1971, 1972, or 1973					

Fiscal 1974 New York Gold Issue melts - Check Assays
ASSAYER'S REGISTER OF MINT FINE GOLD.

DATE 1974	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
2-12	R-10	999.5			
	R-20	6			
	R-30	7			
	R-40	6			
	R-50	6			
	R-60	8			
	R-70	7			
	R-80	7			
	R-90	6			
	R-100	7			
	R-110	7			
	R-120	8			
	R-130	7			
8-9	R-140	7			
	R-150	7			
	R-160	8			
	R-170	7			
	R-180	7			
	R-191	7			
	R-200	7			
	R-210	7			
	R-220	7			
	R-237	6			
	R-248	5			
	R-258	4			
	R-268	4			
	R-278	6			
	R-288	6			
	R-298	6			
	R-368	5			

New York Gold Issue Melts - Check Assays

ASSAYER'S REGISTER OF MINT FINE GOLD.

8-2281

DATE.	NO. OF MELT.	FINENESS.	DATE.	NO. OF MELT.	FINENESS.
1976					
3-22-76	110	999 9			
	120	7			
	130	7			
	140	7			
	150	8			
	160	9			
	169	8			
	178A	8			
	187	998 0			
	200	999 7			

ASSAYER'S REGISTER OF MINT FINE GOLD.

[illegible]

Commercial Bars
Fiscal 1953

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-2231

DATE. 1952	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
11/17	1	9998	-		
	2	9998	-		
11/24	3	9999	-		
1/22/53	4	9999	-		
2/5	5	9999	-		
	6	9999	-		

ASSAYER'S REGISTER OF MINT FINE GOLD.

2-231

DATE.


NO. OF
MELT.


FINESS.


DATE.

NO. OF
MELT.

FINESS.













Assayer's Register of Mint Finegold; 1923-1952

